

REMARKS

Status of the Claims

Claims 1-25 are pending. Claims 16-21, 24, and 25 were withdrawn from further consideration in response to a restriction requirement by the Examiner, under 37 C.F.R. §1.142(b).

In the present Response, claims 22 and 23 are cancelled; and claims 1-15, are amended. Thus, after entry of these amendments, claims 1-15 are presented for reconsideration.

Pursuant to the Office Action, claim 4 is rejected under 35 U.S.C. §112, second paragraph. Claims 1-4 are rejected under 35 U.S.C. §103 for allegedly being unpatentable over *Szczechura et al.* EP 0 486 183 A1 (hereinafter “*Szczechura*”) in view of U.S. Patent No. 5,739,203 to Ngoc (hereinafter “*Ngoc*”) and U.S. Patent No. 5,578,674 to Speth *et al* (hereinafter “*Speth*”). Claims 1-4 are rejected under 35 U.S.C. §103 for allegedly being unpatentable over *Szczechura* in view of both *Ngoc* and *Speth* and further in view of U.S. Patent No. 3,740,262 to *Agostinelli* (hereinafter “*Agostinelli*”) and U.S. Patent No. 4,304,008 to *Joung* (hereinafter “*Joung*”). Claims 1-4 are rejected under 35 U.S.C. §103 for allegedly being unpatentable over U.S. Patent No. 5,997,969 to *Gardon* (hereinafter “*Gardon*”) in view of both *Ngoc* and *Speth*. Claims 1-4 are rejected under 35 U.S.C. §103 for allegedly being unpatentable over *Gardon* in view of both *Ngoc* and *Speth* and further in view of both *Agostinelli* and *Joung*. Claims 1-4 are rejected under 35 U.S.C. §103 for allegedly being unpatentable over U.S. Patent No. 4,199,490 to *Kamiya* (hereinafter “*Kamiya*”) in view of *Ngoc* and *Speth*. Claims 1-4 are rejected under 35 U.S.C. §103 for allegedly being unpatentable over *Kamiya* in view of both *Ngoc* and *Speth* and further in view of both *Agostinelli* and *Joung*. Applicants respectfully traverse all outstanding objections to the specification and rejection of the claims.

Support for the Claim Amendments

Support for the amendments to the claims can be found throughout the specification and claims as originally filed. For example, amended claim 1 is supported at least by page 11, lines 18-21 of the originally-filed specification and by originally-filed claim 8. Amended claim 2 is

supported by originally filed claim 9. Amended claim 3 is supported by originally filed claim 10. Amended claim 4 is supported by originally filed claim 11. Amended claim 5 is supported by originally filed claim 12. Amended claim 6 is supported by originally filed claim 13. Amended claim 7 is supported by at least page 14, line 29, to page 15, line 22. Amended claim 8 is supported by at least page 15, line 23, to page 16, line 12. Amended claim 9 is supported by originally filed claim 12, and 13. Amended claim 10 is supported by originally filed claim 10. Amended claim 11 is supported by originally filed claim 4. Amended claim 12 is supported by originally filed claim 6. Amended claim 13 is supported by originally filed claim 7. Amended claim 14 is supported by originally filed claim 22. Amended claim 15 is supported by originally filed claim 23. Accordingly, Applicants submit that no new matter is introduced by the instant amendments.

Election/Restriction

Applicants acknowledge the election made by telephone with Dr. Gregory P. Einhorn, on August 23, 2002, to the invention of group 1, claims 1-15 and 22-23. However, if appropriate at this juncture, Applicants respectfully request that, after the elected product claims have been found to be allowable, all withdrawn process (methods) claims which depend from or otherwise include all of the limitations of the allowed product claims be rejoined. MPEP §821.04 (7th Ed., Revision 1, Feb. 2000); *In re Ochiai*, 37 USPQ2d 1127 (Fed. Cir. 1995); *In re Brouwer*, 37 USPQ2d 1663 (Fed. Cir. 1995); 1184 OG 86, 3/26/96.

Specification

The Patent Office has objected to the specification alleging that the originally filed specification is replete with grammatical errors that make the determination of the Applicants' invention extremely difficult. Applicants herewith submit a substitute specification, excluding the claims, as required by 37 CFR §1.125(a). While the substitute specification adds no new subject matter, Applicants have provided a marked-up copy of the originally filed specification to show the changes that have been made.

It is noted that claims 5-15 and 22-23 are objected to under 37 CFR §1.75(c) for being in improper form and have not been further treated on the merits. Applicants have amended the claims to present the claims in proper form.

Issues under 35 U.S.C. §112, second paragraph

The Patent Office has rejected claim 4 under 35 U.S.C. §112, second paragraph, for allegedly being indefinite. Applicants have amended claim 4, obviating this rejection. Accordingly, Applicants request reconsideration and withdrawal of this rejection.

Issues under 35 U.S.C. §103

For a proper rejection under 35 U.S.C. §103(a), the references, either alone or in proper combination, must teach or suggest all the claim limitations of Applicants' claimed invention.

Claims 1-4 are rejected under 35 U.S.C. §103 for allegedly being unpatentable over references Szczechura, Ngoc, Speth, Agostinelli, Joung, Kamiya, and Gardon in various combinations as set forth below. Applicants have amended claims 1-4, thereby obviating this rejection as to these claims.

For example, Applicants' claimed invention, in the instant application, is directed to a non-adhesive carboxylated latex product surface-treated with carboxyl-group blocking agents, internally treated with an aluminum inorganic crosslinking agents, or both. In particular, in claims 1, 3, 5, 6, 7, and 8, (as well as claims that depend either directly or indirectly therefrom), the surface of the latex product has been treated with a non-adhesive metal element crosslinking agent having three or more valences, a non-adhesive organic crosslinking agent, a non-adhesive sizing agent, and the compounds of claims 5 or 6, or a non-adhesive surfactant and an internally added aluminum inorganic crosslinking agent. The invention is also directed to a non-adhesive carboxylated latex product internally treated with a carboxyl-group blocking agent comprising an aluminum inorganic crosslinking agent and one or more of the non-adhesive cross linking agent, or compounds of claim 5 or 6 or a non-adhesive sizing agent.

Szczechura discloses a polymer latex for making products having a carboxylated open chain aliphatic diene/acrylonitrile/(meth)acrylate copolymer latex. As acknowledged by the Patent Office, Szczechura does not teach or suggest a non-adhesive carboxylated latex product having the carboxyl-group blocking agents of the instant invention.

Both Ngoc and Speth have been cited to cure the deficiency of Szczechura as an anticipatory reference. Applicants respectfully submit that Ngoc and Speth do not cure the deficiency of Szczechura and, thus, do not present a *prima facie* case of obviousness.

Ngoc does not cure the deficiency of Szczechura because Ngoc does not teach or suggest the non-adhesive latex of the instant invention. For example, Ngoc describes a process for applying a rubbery coating, a plastisol composition, to a substrate. The plastisols are used in the manufacture of articles having good fluid resistance, low temperature flexibility and slip resistance (see column 2, lines 36-39, of Ngoc). In direct contrast, Applicants' claimed invention is to a latex product with a lubricious quality. Accordingly, Ngoc teaches that the compounds, it describes in the reference, can be used to create a non-slip coating. Thus, Ngoc would teach away from using the reagents taught in the reference in the instantly claimed invention. Applicants submit that neither Szczechura nor Ngoc teaches or suggests the carboxylated non-adhesive latex product of the instant invention.

Speth purports to disclose high strength films prepared from aqueous dispersions of block copolymers of vinyl aromatic monomers and conjugated dienes. While Speth teaches the use of surfactants (column 7, lines 47-67, of Speth), it does not teach the use of a surfactant and an internally added aluminum type crosslinking agent. Accordingly, Speth does not teach or suggest a carboxyl-group blocking agent that treats the surface of a latex product and is a non-adhesive metal element crosslinking agent having three or more valences, a non-adhesive organic crosslinking agent, the compounds of claims 5 or 6, or a non-adhesive surfactant and an internally added aluminum inorganic crosslinking agent. Nor does Speth teach or suggest (1) a carboxyl-group blocking agent that is an internally added aluminum inorganic crosslinking agent and (2) any one or more of an internally added non-adhesive sizing agent, non-adhesive surfactant or other compounds of claim 9.

Both Agostinelli and Joung have been cited to cure the deficiencies of Szczechura, Ngoc, and Speth. Agostinelli and Joung describe halogenating the latex product to create a slippery quality to the latex product. However, they also do not teach or suggest a latex product surface-treated with a carboxyl-group blocking agent such as a non-adhesive metal element crosslinking agent having three or more valences, a non-adhesive organic crosslinking agent, the compounds of claims 5 or 6, or a non-adhesive surfactant and an internally added aluminum inorganic crosslinking agent. In addition, Agostinelli and Joung do not teach or suggest (1) a carboxyl-group blocking agent that is an internally added aluminum inorganic crosslinking agent and (2) any one or more of an internally added non-adhesive sizing agent, non-adhesive surfactant or other compounds of claim 9.

Gardon is cited for allegedly disclosing carboxylated latex gloves; however, the Patent Office states that Gardon does not explicitly mention a carboxyl-group blocking agent. Applicants submit that it also does not teach or suggest a latex product surface-treated with a carboxyl-group blocking agent such as a non-adhesive metal element crosslinking agent having three or more valences, a non-adhesive organic crosslinking agent, the compounds of claims 5 or 6, or a non-adhesive surfactant and an internally added aluminum inorganic crosslinking agent. Nor does Gardon teach or suggest (1) a carboxyl-group blocking agent that is an internally added aluminum inorganic crosslinking agent and (2) any one or more of an internally added non-adhesive sizing agent, non-adhesive surfactant or other compounds of claim 9.

The Patent Office further alleges that it would have been obvious to combine Speth or Ngoc with Gardon. For the reasons stated above, assuming Speth or Ngoc could properly be combined with Gardon, they still would not teach or suggest a latex product surface-treated with a carboxyl-group blocking agent that is a non-adhesive metal element crosslinking agent having three or more valences, a non-adhesive organic crosslinking agent, the compounds of claims 5 or 6, or a non-adhesive surfactant and an internally added aluminum inorganic crosslinking agent. In addition, the combination of Speth or Ngoc with Gardon, do not teach or suggest (1) a carboxyl-group blocking agent that is an internally added aluminum inorganic crosslinking agent

and (2) any one or more of an internally added non-adhesive sizing agent, non-adhesive surfactant or other compounds of claim 9.

Kamiya is cited for allegedly disclosing carboxylated latex gloves; however, the Patent Office states that Kamiya does not explicitly mention a carboxyl-group blocking agent. The Patent Office alleges that it would have been obvious to combine Speth or Ngoc with Kamiya. For the reasons stated above, assuming Speth or Ngoc could properly be combined with Kamiya, they still would not teach or suggest a latex product surface-treated with a carboxyl-group blocking agent that is a non-adhesive metal element crosslinking agent having three or more valences, a non-adhesive organic crosslinking agent, the compounds of claims 5 or 6, or a non-adhesive surfactant and an internally added aluminum inorganic crosslinking agent. In addition, the combination of Speth or Ngoc with Kamiya, do not teach or suggest (1) a carboxyl-group blocking agent that is an internally added aluminum inorganic crosslinking agent and (2) any one or more of an internally added non-adhesive sizing agent, non-adhesive surfactant or other compounds of claim 9.

Therefore, Applicants respectfully submit that none of the references, Szczechura, Ngoc, Speth, Agostinelli, Joung, Gardon, or Kamiya, either alone or in proper combination, teaches or suggests each and every limitation of the claimed invention. Accordingly, Applicants respectfully request entry of the instant claim amendments and allowance of the pending claims.

CONCLUSION


It is noted that the Patent Office has made U.S. Patent No. 5,357,636 to Dresdner, Jr. *et al.* of record, but has not been relied upon it, stating only that it is considered pertinent to Applicants' disclosure.

Applicants request that the Examiner reconsider the application and claims in light of the foregoing reasons and amendments and respectfully submit that the claims are in condition for allowance.

If, in the Examiner's opinion, a telephonic interview would expedite the favorable prosecution of the present application, the undersigned attorney would welcome the opportunity to discuss any outstanding issues and to work with the Examiner toward placing the application in condition for allowance.

Applicants believe that no additional fees are necessitated by the present Response. However, in the event any such fees are due, the Commissioner is hereby authorized to charge any such fees to Deposit Account No. 06-1050.

Respectfully submitted,



Joseph R. Baker, Jr.
Reg. No. 40,900

Date: _____

5/2/03

Fish & Richardson P.C.
4350 La Jolla Village Drive, Suite 500
San Diego, California 92122
Telephone: (858) 678-5070
Facsimile: (858) 678-5099



Specification

RECEIVED
MAY 08 2003
TC 1700

Non-adhesive latex products

{Technical Field}

The present invention relates to a novel non-adhesive carboxylated latex product; and to a novel process for manufacturing the same. Further, the present invention provides a latex product with high durability ~~on wear~~.

{Background Art}

Carboxylated latex products ~~—for example, dipping~~ include dipped products such as balloons, gloves, fingerstalls and condoms; extruded products such as rubber threads and rubber pipes; cast- molded products such as balloons and toys; and whole rubber products and products having rubber ~~surfaces~~ surfaces such as rubber sheets, hoses and draw cloths—. Carboxylated latex products are apt to have adhesive surfaces to ~~result in damaging the processability~~ which can negatively affect the manufacturing of the products or producing produce defective articles. Further, they ~~have the defect in that are not ideal for producing~~ products having ~~desirable shapes cannot be fabricated~~ a desired shape such as non-adhesive rolled fingerstalls.

Heretofore, to overcome these defects, adhesion preventing agents have been used, ~~and as the adhesion~~. Adhesion preventing agents have generally been powdered substances ~~are normally used, which are~~ called dusting powder (or simply powder). As ~~the~~ The powder, ~~is generally used~~ are mica, talc, calcium carbonate, white carbon ~~and or~~ corn starch. The powder, however, ~~spreads~~ can spread to ~~an article~~ articles in contact with the latex product and ~~becomes~~ become the cause of various ~~troubles~~ problems if the article ~~belongs to the field of~~ is a precision instrument. Also, ~~the~~ the appearance of the latex product is damaged. In July 1999, ~~the~~ the FDA issued a regulation on medical rubber gloves stating that the powder quantity on synthetic rubber medical gloves should be ~~controlled~~ 120 mg or less per piece of gloves. ~~On the other hand, as to glove~~. For natural rubber medical gloves, the regulation ~~was issued~~ stated that ~~controlled~~ the soluble protein ~~to be~~ 1200- μ g per piece of gloves glove or less to prevent the latex allergy ~~derived~~ resulting from ~~protein~~ the proteins. ~~And, a~~ a shift from natural

rubber gloves to synthetic rubber gloves is anticipated. Thus, making ~~the~~ synthetic rubber products non-adhesive is an important technical issue ~~of the field to be solved~~.

The general method of adhesion prevention, other than the use of powder, includes halogenation by post-chlorination treatment. For example, USP 3,411,982 and 3,740,262 disclose that halogenation makes the surface of rubber gloves slippery. USP 4,304,008 discloses halogenation, in place of ~~the powder~~, facilitates wearing/donning rubber products. USP 3,740,262 discloses halogenating gloves ~~to provide where~~ the outside surface ~~without the~~ is powder-free and the inside surface ~~with the powder is~~ powdered.

~~The halogenation~~ Halogenation is a method in which a thin layer of halogenated rubber is made/formed on the product surface to prevent adhesion and blooming, ~~and this~~. This method is fairly widely ~~conducted~~ used, providing a rubber product having a clean surface ~~without the~~ free of powder. However, when the degree of halogenation is too high, discoloration ~~occurs~~ can occur, the surface ~~becomes~~ can become brittle ~~to and~~ cause cracks, or heat resistance is ~~deteriorated~~ can deteriorate. Further, ~~it there~~ is feared for the danger that any contacting metal ~~to may~~ be corroded. Above all things, many users hesitate to use such products because of their ~~being environmentally undesirable~~ negative environmental impact.

USP 4,304,008 discloses surgical gloves wherein the inside layer comprises a natural rubber and the outside layer a halogen-resistant silicone, ~~the~~. The inside layer ~~being is~~ halogenated to give a non-adhesive property.

The ~~defect~~ deficiencies of halogenation is ~~admitted by~~ are set forth in USP 5,284,607. In the patent, medical gloves are formed using an acid-soluble powder, which is then dissolved by treating with an acid such as nitric acid. Thereafter, ~~and thereafter~~ the gloves are chlorinated by a bleaching agent.

There are ~~found~~ a variety of improvements in the methods ~~offor~~ for manufacturing rubber products, which use powders or substances having particulate structures.

USP 4,070,713 discloses medical gloves comprising two layers, i.e., outside and inside layers, of elastic substances. In the inside layer, a particulate substance such as zinc oxide ~~on or~~ titanium oxide is firmly embedded, and ~~moreover on the inside surface~~ partially exposed to come in contact with the skin, ~~the particles are exposed partially~~.

USP 4,143,109 discloses a ~~manufacture~~manufacturing method ~~relating~~related to the above-mentioned patent.

USP 5,138,719 discloses a method for making powder-free gloves, fingerstalls and the like from latex and ~~microcapsule~~microcapsules. The ~~microcapsule~~microcapsules are dispersed and distributed in the latex so that ~~its~~their concentration may increase from the outside surface of the product toward the inside surface thereof, to build a concentration gradient. The microcapsule concentration is high on the inside surface, and this gives a good ~~slipping~~lubricious property and ~~an easy wearing ease in donning~~ without the use of powder.

USP 5,881,386 discloses gloves having two layers, with the two layers comprising ~~polyvinyl chloride~~ polyvinyl chloride and polyesterpolyurethane. The inside polyesterpolyurethane layer is incorporated with a particulate substance of 1 to 75 μm.

Japanese Patent Application Laid-Open (Kokai) No.11-12823 discloses, ~~regarding the working gloves for clean room manufactured from polyvinylidene chloride paste sol~~, a technology ~~offer~~for manufacturing working gloves with improved dusting properties by dipping ~~them in an~~the inside surface in a treating agent containing a powder of 0.1 to 1.5 μm followed by drying. The working gloves, used for clean rooms, are manufactured from polyvinylidene chloride paste sol.

Japanese Patent Application Laid-Open (Kokai) No.11-61527 discloses rubber gloves excellent ~~in wearing~~for donning and ~~removing~~doffing, which ~~are provided with~~have a slippery resin layer ~~by dipping, having been dipped~~ in an aqueous dispersing liquid containing a synthetic rubber latex that is not coagulated by a coagulant contained in the gloves themselves, and containing an organic filler.

Japanese Patent Application Laid-Open (Kohyo) No.9-501983 discloses a water-~~dispersable~~dispersible silicone modified dispersion powder composition and ~~the~~a method of manufacturing it, and describes that the composition can be used as an antiblocking agent.

In recent years, ~~such~~ products have ~~come to be~~been developed ~~that~~with various substances ~~are~~ coated on the surface of latex products.

USP 4,310,928 provides surgery gloves by dispersing an oil and fat or lipophilic substance in a coagulation liquid and coating it on the surface of a natural rubber. ~~Here, to~~ To prevent separation of the oil and fat or lipophilic substance, a surface active agent is added ~~into~~ to the coagulation liquid.

USP 5,780,112 and 5,974,589 disclose a method of attaching a high density straight-chain hydrocarbon polymer, ~~especially in particular~~ polyethylene, to the surface of a natural rubber by chlorine generated by acidifying a hypochlorite, ~~and the~~. The latex product thus treated is non-adhesive without the use of powder.

Japanese Patent Application Laid-Open (Kohyo) No.11-507085 discloses a flexible copolymer coating which can be bonded firmly to the surface of a rubber article and extend, without separation, from the bonded surface. The patent, taking into consideration the ~~removal property~~ need to remove the latex product from the dipping former and ~~the dry and wet wearing property~~ conditions, discloses an emulsion type copolymer between a reactive, low surface energy monomer, preferably a silicone oligomer, and an alkyl acrylate and a reactive hard monomer.

There are many disclosures on the ~~method~~ methods for preparing the powder free gloves by coating a hydrophilic hydrogel forming polymer on the rubber surface and curing the polymer layer. ~~The examples thereof are~~ Examples include USP 3,326,742; 3,585,103; 3,607,473; 3,745,042; 3,901,755; 3,925,138; 3,930,076; 3,940,533; 3,966,530; 4,024,317; 4,110,495; and 4,125,477.

Further, USP 4,499,154 discloses a method of manufacturing a talc-free product by immersing a dipping former in a natural rubber latex, leaching the product in hot water, impregnating the product with a dilute acid, neutralizing the surface with water or an aqueous alkali solution, dipping in a hydrophilic hydrogel formable polymer such as a copolymer of 2-hydroxyethylmethacrylate and methacrylic acid or 2-ethylhexylacrylate and a crosslinking agent thereof, heating the ~~coat~~ polymer layer to fix it to the rubber, vulcanizing the rubber, removing the product from the dipping former, coating it with a silicone containing a surfactant, and providing heat. This method also discloses that the ~~slipping~~ lubricious property for wet hands is improved by crosslinking the ~~coat~~ layer of the hydrogel polymer of the invention and, thereafter ~~by~~, treating it with a cationic surfactant such as a long chain aliphatic amine. The patent also discloses that impregnating the rubber surface with an aluminum salt after acid

treatment is preferable. This method can ~~afford~~produce powder-free rubber products, but it includes many steps and raises the manufacturing costs excessively ~~and~~. ~~Moreover,~~ it cannot be ~~adopted~~used for ~~the product~~products, which ~~dislikes the contamination of~~should not include silicone.

USP 4,575,476 discloses that the coat layer of a specific 2-oxyethyl methacrylate hydrogel polymer that has a good ~~slipping~~lubricious property for use with dry hands. Further, by treating the above-mentioned hydrogel ~~coat-layer~~ with a surfactant, ~~especially in particular~~ with a cationic surfactant and a long chain aliphatic amine, the ~~slipping~~lubricious property for use with wet hands is improved.

Furthermore, by treating the product with a silicone containing surfactant, the adhesiveness of the surface, without the hydrogel ~~coat-layer~~, is markedly improved.

USP 5,688,855 discloses that the hydrophilicity of a solid surface gives lubrication to the surface in the presence of water, and that a hydrophilic concentration gradient is automatically generated within ~~the coat-layer~~a coating by dissolving in one solvent a hydrogel forming polymer component and a water-soluble polymer component that has a low compatibility with the ~~above~~former component, coating them on the surface of a rubber product, and evaporating the solvent to cause phase separation of the two components.

Japanese Patent Application Laid-Open (Kokai) No.11-269708 discloses gloves laminated with a lubricant layer of a rubber or resin containing collagen on the inside surface of gloves provided with a base layer of a rubber or polymer. ~~The defect of~~ One problem with coating ~~on~~ the rubber surface is that layer separation ~~occurs~~can occur when the rubber is extended.

USP 4,499,154 discloses reinforcing the adhesion of ~~the coat-layer~~a coating by undercoating an acid on the rubber surface.

WO93/06996-A1 proposes using, as a ~~coat-layer~~coating, a polymer having a repeated structure of specific ether ~~group~~groups and ester ~~group~~groups.

USP 4,548,844 discloses ~~an improvement of~~improved adhesion between a rubber layer and a hydrogel layer through acid treatment ~~and~~. It also discloses that, by undercoating an aluminum cation or a cation of trivalence or more, prior to the coating of the hydrogel polymer or by adding it to the hydrogel polymer, the adhesion of the rubber layer and the hydrogel polymer is enhanced. It is presumed that this is caused by

~~bonding of~~ a hydroxy or carboxyl group in the hydrogel polymer being bonded to a protein in the rubber latex.

Japanese Patent Application Laid-Open (Kokai) No.6-70942 discloses a multilayer product comprising a first layer formed from a natural rubber, a second layer of a natural rubber, polyurethane, poly(acrylamide/ acrylic acid) and polyethylene oxide, and a third layer of an acryl copolymer and fluorocarbon telomer resin. The product ~~is wearable~~can be donned under dry or wet conditions without the use of powder.

Japanese Patent Application Laid-Open (Kokai) No.10-95867 discloses production of powder-free medical gloves by coating a lubricating composition comprising ~~the~~a first and second ~~ingredients~~composition on the surface of an ~~elastomer~~elastomeric product on the wearer's side ~~with which the elastomer product is contacted.~~ Here, the inside. The first composition comprises at least one compound selected from the group consisting of acetylene diol, organosilicone, amino modified silicone, and cationic surfactant. The second composition is at least one compound selected from the group consisting of cationic surface active agent, organosilicone, amino-modified silicone and acetylene diol.

Japanese Patent Publication (Kokoku) No.7-4405 discloses a method of treating a surface with a modified polysiloxane.

The methods for manufacturing rubber products containing no dusting powder ~~includes the~~include a method in which a bivalent coagulant metal salt, such as calcium nitrate, and a latex stabilized by adding a water soluble surfactant stable against the ~~said~~ metal salt, preferably a nonionic surfactant, or a resin polymer, are brought into co-existence in a coagulation liquid, ~~and the~~. A dipping former, coated with the ~~said~~ coagulant, is dipped in the latex to coat ~~the one side of the rubber product~~. Although this method fails to make the rubber product substantially non-adhesive, it is possible to make the rubber product non-adhesive by adding a peeling or anti-adhesion agent to ~~such the~~ coagulant composition as ~~the~~a third component.

USP 3,286,011 and 3,411,982 to Kavalir et al. disclose ~~such technology~~the above mentioned technology. The ~~patent~~patents, however, ~~fails~~fail to make the product powder-free because it ~~adopts the~~uses powder as the peeling agent.

The ~~patent discloses~~patents disclose that polyvalent metal salts like calcium, magnesium and aluminum can be used as the latex coagulants.

The above-mentioned USP 4,310,928 discloses a method of fabricating surgery gloves, which can be removed from a dipping former by dispersing a lipophilic substance into ~~at the~~ coagulant liquid, such as calcium nitrate ~~by using such a coagulant~~.

Japanese Patent Application Laid-Open (Kohyo) No.10-508899 discloses a method for producing a rubber article ~~freed from the~~free of powder by adding to the coagulant, an acrylic emulsion copolymer coating composition and a silicone emulsion. The ~~said~~ coating composition is made by copolymerization of a reactive silicone acrylate, an alkyl acrylate and a hard monomer, but such a composition is a known substance. The patent clarifies that the release becomes easy only when the silicone emulsion is added to the composition and that the gloves ~~shows excellent~~performs well under dry-type and wet-type wearing performance conditions.

EP 640,623 discloses a coagulant for natural rubber comprising a salt-stable polychloroprene or polyurethane and a bivalent metal salt ~~and to that powder~~. Powder-free rubber gloves can be manufactured by further adding ~~into~~ the coagulant a peeling agent consisting of a polyethylene wax emulsion and a cationic surfactant.

In Japanese Patent Application Laid-Open (Kokai) No.11-236466236466, surfactants and various waxes such as polypropylene wax emulsion ~~in place~~, instead of the polyethylene wax emulsion, were employed as an adhesion eliminating agent or releasing agent, ~~wherein the~~. The cationic surfactant functions ~~for stabilizing~~ to stabilize the polychloroprene added to the coagulant and functions as a ~~releaser~~releasing agent between the polychloroprene and the dipping former ~~because the~~, having a greater affinity for the dipping former ~~is higher than that for the pertinent polymer~~.

Japanese Patent Publication (Kokoku) No.2-42082 discloses a coagulant composition formed by adding a latex, and a surfactant or bivalent or trivalent metal salt into water.

In Japanese Patent Application Laid-Open (Kohyo) No.9-511708511708, the Teague method is ~~adopted to~~used in the manufacture of polyurethane coated gloves. Namely, a first layer is formed by dipping a former in an aqueous dispersion liquid or emulsion of a polyurethane polymer or copolymer, ~~and the~~. The first layer is dipped in

a coagulant then a latex compound to form a second layer. This ~~literature~~application also discloses a method of forming a lubricating polymer layer ~~on~~over the second layer.

There is disclosed technology ~~regarding to~~for making two powder-free gloves which use novel raw materials.

USP 5,851,683 proposes a special successive copolymerization polymer ~~as-to~~make powder-free gloves comprising a thermoplastic elastomer for use in clean roomrooms.

~~As mentioned above, the method~~ Methods of preventing the adhesion of emulsion /latex products ~~is~~are important ~~into~~ both sides of ~~manufacture~~manufacturing and use of the products. Although various proposals have ~~appeared~~been advanced, many of ~~such~~these technologies are considerably complicated ~~and such a~~. A method that is simple, effective and economical has not been developed. One reason for this is that, ~~since the main material is a natural rubber latex, a natural substance having with a strong adhesion and~~adhesive property with complicated causes for ~~the~~creating adhesion. Due to this, the treatment materials and techniques for ~~the~~preventing adhesion ~~prevention~~ possibly ~~become~~can be complex.

The present invention, taking into consideration the above-mentioned current status of adhesion treating technology, ~~is to provide a~~provides novel powder-free, non-adhesive carboxylated latex ~~product~~products and ~~to a novel method~~methods of manufacturing the same. Further, the present invention provides ~~a latex product~~products having excellent durability ~~in wear~~ without sulfur vulcanization.

{Disclosure of the Invention}

~~We studied intensively~~ In our intense study to solve the above-mentioned problems, ~~and how found~~we discovered that the ~~adhesion~~adhesiveness of the surface of the latex product is strong if the surface of a ~~carboxylated~~carboxylated latex product is not sufficiently crosslinked with a bivalent metal compound as a coagulant ~~and further that, even~~. Furthermore, if sufficient crosslinking is conducted with a mono- or bi-valent metal compound, the resulting non-adhesion is insufficient since heating ~~causes the~~can cause adhesion between the ~~inner and outer surfaces of the latex product~~products. Assuming that the cause of the adhesion of a carboxylated latex product may lie in that

the carboxyl group of the latex forms a hydrogen bond through water, we studied methods to inhibit this hydrogen bond formation.

We first studied use of a metal compound having tri- or more valence as an external crosslinking agent. For example, ~~an~~ aluminum salt ~~which is~~, a representative trivalent metal cation, possesses a very strong coagulating ability according to the Shultz-Hardy Law, ~~but~~. But, when only aluminum compound is used as the external coagulant for the purpose of making a dipped product, only ~~the~~ an extremely thin film is formed. However, we found that a ~~dip~~ film having ~~a usual~~ an acceptable thickness ~~is~~ can be formed by forming a layer of an external crosslinking agent of aluminum compound on a dipping former, followed by ~~forming thereon~~ a coagulant layer of ~~a usually~~ the normally used mono- or bi-valent metal salt, then dipping it into the latex solution ~~and further found that~~. In this procedure, the aluminum compound crosslinking layer is formed in the innermost layer. ~~Further surprisingly~~ Surprisingly, it was found that the inside surface of the ~~dip film~~ dipped product crosslinked with the aluminum compound is non-adhesive and that bringing each of the inside surfaces into close contact followed by heating under wet conditions does not cause ~~the adhesion of~~ them to adhere to each other.

On the other hand, when the external crosslinking agent layer of the aluminum compound is formed on the external coagulant layer of mono- or bi-valent metal salt and subsequently dipped into the latex solution, only a thin film is formed. However, when external crosslinking agent layer is formed on the external coagulant layer ~~comprises~~ comprising a mixture of the mono- or bi-valent metal salt and the aluminum compound followed by dipping in the latex solution, surprisingly a film having ~~usual~~ the normal thickness and a non-adhesive inside surface is formed.

Next, we studied ~~on~~ making the outside surface of the ~~dip film~~ dipped product non-adhesive. A film was shaped by forming the external coagulant layer on the dipping former and dipping it into the latex. The film was further dipped into the aluminum compound solution according to the usual method, followed by heating, thereby forming ~~any~~ an aluminum compound crosslinking layer on the outside surface of the film. The outside surface of the film was non-adhesive. Further, after releasing the ~~dip~~ dipped product from the dipping former, ~~the~~ both surfaces were dipped in the

aluminum compound solution and subjected to subsequent heating. ~~The both~~Both surfaces were found to be non-adhesive.

Based on the above-mentioned findings, the crosslinking layer formation reaction of the latex surface was tested using various compounds of metal elements having three or more valences, ~~and it.~~ It was found ~~to~~that they could be possibleused to produce a latex article having a non-adhesive surface.

Furthermore, we tested ~~fortreating the surface treatment~~ of the latex base substance with various organic crosslinking agents that crosslink the carboxy group of the carboxylated latex in the same manner as ~~with the metal compound~~compounds having three or more valences. ~~As the result, it was confirmed~~The results, showed that the organic crosslinking agent ~~gave~~agents produced non-adhesive latex products as ~~with~~did the tri- or more valent metal ~~compound~~compounds. Emulsion type crosslinking agents tended to ~~give high effect, and, even if considered as the crosslinking agents of the same type,~~have a large effect, while water soluble organic crosslinking agents showed ~~low effect~~less of an effect. This held true even when the cross linking agents were of the same type. Moreover, the latex film formed by the dipping method ~~by adding~~using the water-soluble crosslinking agent added to the coagulant raised problems in that cracks developed, and the film strength was poor ~~and so forth, to name a few~~. Presumably, the crosslinking agent diffused into the inside of the film to cause ~~the so-called over-vulcanization, which brought forth the deterioration of~~in the strength of the film.

We ~~tested for addition of~~added chemicals having a coagulating effect to the emulsion latex in order to prevent the diffusion of the crosslinking agent, and confirmed that the ~~undermentioned internal addition use aluminum type~~internally added inorganic aluminum crosslinking agents such as aluminates and aluminum hydroxide gels (also referred to herein as "aluminum type inorganic crosslinking agents") could be added to the emulsion latex without coagulating the carboxylated latex. In addition, the latex film that was not made non-adhesive in the treatment with a concentration as high as 1% of a water-soluble crosslinking agent such as oxazoline crosslinking agent, e.g. Epocross W (made by Nippon Shokubai), was made non-adhesive when ~~such a~~ compound having ~~coagulation~~a coagulating effect was added even in a concentration as extremely low as 10 ppm.

~~As to the system in which the internal addition use~~ As used herein, “external,” when used in conjunction with a compound, refers to the fact that the compound is not added to the latex. “Internal” refers to the fact that the compound is added or incorporated into the latex.. ~~The effect of the diffusion of organic crosslinking agents when an internally added~~ aluminum type inorganic crosslinking agent, such as aluminate or aluminum hydroxide gel was, is added to an emulsion latex, ~~the effect of the diffusion of organic crosslinking agents was studied further.~~ After forming a film with the coagulant containing organic crosslinking agent, the effect on the film strength ~~of~~ based on the temperature ~~of~~ at the leaching stage was examined. ~~As a result, the~~ The film strength ~~lowered in~~ decreased at the usual leaching stage temperature of 50 to 60°C, but ~~the~~ a decrease ~~of the~~ in film strength was not observed when the treatment ~~of~~ at the leaching stage was conducted at 70°C or more. Presumably, unlike the tri- or more valent metal ~~compound~~ compounds in the coagulation liquid, the crosslinking agent in the aqueous treatment solution, being poorly reactive with the carboxyl group in the latex at a low temperature, diffuses toward the Z-axis direction ~~without staying and does not stay~~ on the surface of the latex product ~~to cause the, causing a deterioration of the~~ film strength.

~~With~~ The effect of decreasing the concentration of the organic crosslinking agent ~~decreased, its effect,~~ on the adhesion and strength of the latex product was examined. Even with a concentration of the organic crosslinking agent as extremely low as 0.001% (2×10^{-4} part per latex solids), the latex product showed non-adhesion, and the strength of the product was equivalent ~~with~~ to that of the untreated product. The effect of the organic crosslinking agents on the strength differs according to the properties ~~thereof~~ of the crosslinking agent. Those which have a lower degree ~~for the~~ of diffusion ~~to~~ in the Z-axis direction, or those ~~which~~ that react immediately on the surface of the latex and do not diffuse ~~into the inside~~ internally, exert less influence on the product strength.

~~On the other hand, we~~ We conducted a ~~wearing~~ durability test for fingerstalls ~~prepared in the test.~~ The A fingerstall obtained by vulcanizing the carboxylated latex with zinc oxide, although showing good results in the strength test, was found to be very poor in durability since the film developed cracks ~~on wear from~~ in several hours to ~~within~~ one

day of wear. This is because the defect of ion crosslinking ~~surfaced up~~ comes to the forefront on the surface of the fingerstalls.

We conducted a ~~wearing~~ durability test for the above-mentioned fingerstalls, which were obtained by adding an internally added aluminum type inorganic crosslinking agent such as aluminate or aluminum hydroxide gel to an emulsion latex. Unexpectedly, they did not ~~break~~ tear when worn for a period from one day to one week. This is thought to be because, when the ion crosslinking by zinc oxide ~~cleaves on~~ cleaved upon use, the aluminum ion retaining crosslinking power repairs the cleaved points. Thus, by adding the internally added aluminum type inorganic crosslinking agent such as aluminate or aluminum hydroxide gel into the carboxylated latex, ~~the~~ non-adhesion ~~adhesive~~ treatment becomes possible even with an extremely low concentration of the organic crosslinking agent that hitherto has been incapable of use in non-adhesion treatment ~~treatments~~. Further, it becomes possible to produce latex products excellent in durability without sulfur vulcanization.

~~The retesting~~ Tests on tri- or more valent metal compound crosslinking agents gave similar results.

Other organic crosslinking agents for carboxyl ~~group~~ groups ~~can~~ make the carboxylated latex product non-adhesive at a lower concentration, as in ~~the said~~ oxazoline type crosslinking agents.

Organic compounds, which are not crosslinking agents for carboxyl ~~group~~ groups but are considered to react with carboxyl ~~group~~ groups, have similar effects. Such compounds include glyoxal, polyamide compound, polyamide polyurea compound, polyamide polyurea glyoxal condensation reaction product, polyamine polyurea compound, polyamideamine polyurea compound, polyamideamine compound, polyamideamine epihalohydrine condensation reaction product, polyamideamine formaldehyde condensation reaction product, polyamine epihalohydrine condensation reaction product, polyamine formaldehyde condensation reaction product, polyamide polyurea epihalohydrine condensation reaction product, polyamide polyurea formaldehyde ~~condensation~~ condensation reaction product, polyamine polyurea epihalohydrine condensation reaction product, polyamine polyurea formaldehyde condensation reaction product, polyamideamine polyurea epihalohydrine condensation reaction product, and polyamideamine polyurea formaldehyde condensation reaction

product. These compounds have been developed as waterproof endowing agent, sizing agent, printability improver, wet strength enhancing agent, and paper strength reinforcing agent of papers, and ~~are common in that any of them is a chemical~~ share the trait that they are all chemicals for controlling hydrogen bonds in ~~the~~ paper.

Next, we studied compounds such as monofunctional epoxy compounds and monofunctional amines that do not crosslink with the carboxyl group of the latex, but that react with the carboxyl group to inhibit the formation of hydrogen bond derived from the carboxyl group.

As a result, it was confirmed that these compounds, which are considered to bond to a carboxyl group ~~to lead~~ leading to hydrophobicity, afford similar effects to those of the before-mentioned compounds.

We studied ~~on~~ sizing agents, which are used in the field of paper as ~~chemical~~ chemicals to block carboxyl groups. The typical example of ~~the~~ a sizing agent is the rosin type, ~~and the~~ The main ingredient of rosin is abietic acid. ~~The rosin~~ Rosin coats pulp fibers and exhibits excellent hydrophobicity ~~at that time~~. The contact angle of rosin and water ~~is~~ can be as large as 53° , ~~and if~~ If aluminum is bonded, the contact angle becomes as extremely large as 130° . Thus, ~~the rosin gives a large effect as~~ rosin is a hydrophobicity endowing agent. The rosin sizing agent was tested in the same manner as the above-mentioned compounds, and ~~the~~ its effect as a blocking agent of carboxyl group was confirmed. ~~The effect of the sizing agent is thought~~ This effect of the sizing agent may be because it coats the latex surface physico-chemically or physically into hydrophobicity, ~~and it~~ It is estimated theorized that aluminum ion plays a big role in this action.

Further, in recent years, ~~as the sizing agent for neutral paper there are used~~ alkylketenedimer(AKD), alkenylsuccinic acid anhydride(ASA), cationic sizing agent, and the like have been used as sizing agents for neutral paper. These neutral sizing agents also had a similar effect on non-adhesiveness. Regarding the hydrophobicity ~~effect~~ effect of AKD and ASA, it is ~~said~~ generally believed that they create hydrophobicity by chemically bonding to a hydrophilic group. But, there is a view that they cause autolysis on the surface of ~~fiber~~ fibers to lose hydrophilicity and the whole compound becomes hydrophobic. ~~In this time~~ Thus, the hydrophilic group works as anchor. In any event, it is evident that the relevant sizing agent blocks the carboxyl

group on the latex surface chemically, physico-chemically or physically to generate hydrophobicity of the surface.

We also studied ~~on~~ making the surface of latex products hydrophobic chemically or physically, taking the above-mentioned hydrophobicity effect into consideration. First, we ~~had an eye~~ looked to the hydrophobic group of surfactants and examined ~~on~~ nonionic surfactants. As ~~the results~~ a result, it was found that HLB, an index of hydrophilicity and hydrophobicity, could not interpret the degree of non-adhesion. Further, cationic and amphoteric surfactants do not have ~~even~~ such an index. We thought it convenient to determine the propriety by conducting adhesion test 1 or 2 as shown in the below-mentioned examples. The surfactant that showed a non-adhesion adhesive effect is called hereinafter a non-adhesive surfactant.

The anionic surfactant has a an effect similar ~~effect as the said surfactant~~ to the cationic and amphoteric surfactants. However, the anionic surfactant loses the function of a surfactant as soon as it forms a metal soap with polyvalent metal salts derived from a coagulant. Many of the metal salts of the anionic surfactants have ~~adhesiveness~~ adhesiveness, and the treatment with an anionic surfactant sometimes ~~gives~~ produces an adverse effect. To grasp the characteristics of the compound itself, it is necessary to conduct the adhesion test.

For the surfactant to exhibit the non-adhesion adhesive effect, it is necessary to add an internally added aluminum type inorganic crosslinking agent such as aluminate or hydroxyaluminum gel directly into an emulsion latex.

We further studied, based on the above-mentioned findings, ~~the~~ a method of directly adding a carboxyl-group blocking agent into a carboxylated latex. When an article is made by the dipping method, the latex film, after the dipping, is extracted with hot water ~~on~~ at the leaching stage. Accordingly, the carboxyl-group blocking agent incorporated in the latex ~~liquefies~~ leaches out ~~on~~ at the leaching stage, failing to ~~fail in making~~ make the carboxylated latex product non-adhesive. On the other hand, when the carboxyl-group blocking agent is an emulsion type, when it reacts with a carboxylated emulsion latex, or when it is adsorbed on a carboxylated emulsion latex, it reacts with a bivalent metal salt, preferably calcium salt, in the coagulant and it ~~does~~ does not ~~liquefy~~ leach out. In ~~ease~~ cases where there is a special condition such that the ~~carboxyl~~ carboxyl group blocking agent does not ~~liquefy out, for example,~~ leach out,

incorporating the carboxyl-group blocking agent into the carboxylated emulsion latex gives a non-adhesive product. Example of a special condition includes a condition that the calcium soap formed above has a non-adhesionadhesive effect or a condition that the carboxyl-group blocking agent does not liqueateleach out by reacting with the aluminum type inorganic crosslinking agent such as aluminate or aluminumhydroxide gel added in the carboxylated emulsion latex,~~only incorporating the carboxyl-group blocking agent into the carboxylated emulsion latex gives a non-adhesive product.~~

We also studied ~~earnestly~~ techniques for making carboxylated latex products non-adhesive through chlorination. Chlorination, wherein chlorine adds to the double bonds of rubber molecules on ~~the~~ both surfaces, outside and inside, of carboxylated latex products, produces, ~~so to call it, a coat~~ a layer of chlorinated hydrocarbon, though it ~~poses problems regarding~~ raises environmental ~~measures~~ concerns.

For this reason~~the~~, both surfaces of the rubber products lose ~~the~~ their rubbery properties, ~~presenting hydrophobicity~~ leading to the hydrophobic and non-adhesion~~adhesive~~ surfaces. There are many problems in ~~view of the manufacture~~ manufacturing, which ~~derive from~~ are affected by the quality of chlorination, ~~and a~~. A big problem in the manufacturing process is that on-machine chlorination ~~on the~~ of both sides, ~~with an article to be chlorinated being attached to a former, is not possible, since one side of the article to be chlorinated is attached to the former.~~ Usually~~the~~, chlorination is conducted ~~on~~ as a separate step after the product has been removed from the former, ~~or conducted on a separate step, after on-machine chlorination of only the outside surface, with the product removed from the former and with its inside surface reversed outwardly.~~ This ~~inevitably deteriorates~~ step reduces production efficiency.

We have found the problem can be solved by a method wherein ~~provision of non-adhesion to~~ of the outside surface is ~~earr~~ yingcarried out by on-machine chlorination and ~~provision of non-adhesion to~~ of the inside surface is carried out by adopting a non-adhesion providing technique separately invented by us (JP Application No. 2000-139733).

The techniques for providing non-adhesion to carboxylated latex products have been mentioned above. By chlorinating the outside surface of the carboxylated latex products, which had been manufactured by using such techniques, it was possible to

produce non-adhesive carboxylated latex products. In ~~case that~~ cases where the products are rubber gloves, they are turned inside out when they are removed from the former. Consequently, the inside surface has been subjected to chlorination, and gloves that are good in ~~wearing~~ donning and ~~removing~~ doffing are fabricated.

The carboxylated latex film, which has been ~~through with~~ subjected to non-adhesion measures as to the inside surface, can be on-machine chlorinated by ~~dipping~~ being dipped into a chlorine aqueous solution or by contacting the outside surface with chlorine gas. The outside surface of the chlorinated carboxylated latex products is then non-adhesive, and the inside surface thereof is non-adhesive through the non-adhesion providing treatment provided herein.

Further, in the case of gloves, they are ~~turn~~ turned inside out when they are peeled off from the former, and the inside surface corresponds to the surface that has undergone the chlorination. For this reason, ~~wearing~~ donning and ~~removing~~ doffing the gloves are easy. As used herein, the outside surface in the present invention ~~means a face~~ is the surface that ~~does~~ is not in contact with the former in the dipping process, and the inside surface ~~means~~ is the one that ~~contacts~~ is in contact with the former.

~~The chlorination~~ Chlorination of the outside surface can be effected by ~~any~~ any known method. That is, ~~such~~ methods can be adopted in which a formed carboxylated latex film is dipped in a chlorine aqueous solution or put into direct contact with chlorine gas. Since only one side is to be chlorinated, it can be performed by ~~means of~~ on-machine means.

As mentioned above, it is possible by using the present invention to fabricate the latex product, which is non-adhesive in one or both surfaces thereof. The surfaces of such products do not ~~attach~~ adhere together even when ~~each one~~ one surface comes in contact with the other under ~~heating~~ heat during and after ~~the manufacture of them~~ manufacturing. Accordingly, ~~a product can be produced that has never~~ products are provided that have not existed until now.

One ~~of such products~~ product is a non-adhesive fingerstall mechanically wound on-machine ~~from its mouth~~ before removing from the dipping former. ~~The~~ A fingerstall wound ~~from the mouth has been existed until now~~ upon itself is known, and its usefulness has been recognized because of its ~~easy to wear~~ ease of use. However, ~~the~~ both surfaces of the fingerstall, a latex product, are intrinsically adhesive, and in order

to manufacture the wound product, the fingerstall had ~~previously~~ to be made non-adhesive by a treatment such as powdering and post-chlorination, followed by winding with human hands. This made it impossible to maintain the ~~cleanness~~cleanliness of the product ~~in a high level and it was difficult to use such a product, which would affect its ability to be used~~ in a workplace, such as a clean room, where precisely processed articles are manufactured. In ~~contrast~~contrast, the present invention, which is able to make ~~the~~ both surfaces of a formed latex non-adhesive, can provide a method ~~to mechanically wind~~for mechanically winding (rolling) a fingerstall on a dipping former and can, thus, maintain the ~~cleanness~~cleanliness of the product to a high degree.

Recently, ~~a thin fingerstall is~~fingerstalls are desired since wearing ~~a thick one~~tends ~~ones tend~~ to cause ~~tiredness~~exhaustion. The thinner the fingerstall, however, the more difficult ~~to wear it, so it is to don~~. Therefore, what is desired is an easy to don wound fingerstall that is thin, powder-free, non-adhesive and clean. By utilizing the property that ~~the~~ both surfaces of the fingerstall are non-adhesive, a fingerstall with ~~wound mouth~~a rolled lip can easily be manufactured. In manufacturing the fingerstall, the top of the stall ~~is~~can be left adhesive ~~without~~by not providing ~~the~~it a layer of carboxyl-group blocking agent, thus, the whole ~~is~~fingerstall can be wound up, and then unwound. By this, the adhesive portion remains as ~~wound mouth~~the rolled lip.

Hitherto, the ~~wound mouth has been~~rolled lip was formed first by winding up only the top of the stall to make the ~~wound mouth~~rolled lip, and, thereafter, the stall ~~must have been~~was released from the former in another step. The ~~wound mouth~~rolled lip facilitates ~~wear~~donning and ~~removal~~doffing of the stall and is highly desired for flat products. Further, after formation of the ~~wound mouth~~rolled lip by the conventional method, a non-adhesion treatment may be conducted. This procedure is also applicable to the wound fingerstall described in the preceding paragraph, thereby providing the fingerstall with ~~wound mouth~~a rolled lip.

The present invention relates to:

(1) A non-adhesive carboxylated latex product incorporated with a carboxyl-group blocking agent;

a. (2) A non-adhesive carboxylated latex product having a layer treated with a carboxyl-group blocking agent on one or both surfaces of a

carboxylated latex product or a carboxylated latex product incorporated with a carboxyl group blocking agent;

(3) A non-adhesive carboxylated latex product having a layer treated with a carboxyl group blocking agent on the inside surface of a carboxylated latex product or a carboxylated latex product incorporated with a carboxyl group blocking agent and having a chlorination treatment on the outside surface;

b. (4) A non-adhesive carboxylated latex product according to (1) to (3), wherein the carboxylated latex is ~~NBR, SBR, CR or MBR, acrylonitrile – butadiene rubber (NBR), styrene – butadiene rubber (SBR), chloroprene – rubber (CR), or methyl methacrylate – butadiene rubber (MBR);~~

(5) A durable, non-adhesive carboxylated latex product according to (1) to (4), wherein the carboxylated latex is added and crosslinked with an internally added aluminum-type inorganic crosslinking agent;

(6) A non-adhesive carboxylated latex product according to (1) to (5), wherein the latex product is a ~~dip~~dipped product;

(7) A non-adhesive carboxylated latex product according to (6), wherein the ~~dip~~dipped product is a fingerstall, ~~gloves~~glove, balloon or condom, —;

(8) A non-adhesive carboxylated latex product according to (1) to (7), wherein the carboxyl-group blocking agent is a metal element crosslinking agent having three or more valences;

(9) A non-adhesive carboxylated latex product according to (8), wherein the metal element crosslinking agent having three or more valences includes at least one compound selected from aluminum, titanium or zirconium compounds;

(10) A non-adhesive carboxylated latex product according to (1) to (7), wherein the carboxyl-group blocking agent is an organic crosslinking agent for the carboxyl group of the carboxylated latex;

(11) A non-adhesive carboxylated latex product according to (10), wherein the organic crosslinking agent for the carboxyl group includes at least one compound selected from aziridine compounds, epoxy ~~compounds~~compounds, blocked isocyanates, oxazoline compounds, carbodiimido compounds, melamineformaldehyde resins, ureaformaldehyde resins, isocyanates, phenolformaldehyde resins, glycols, polyols, diamines, polyamines, hexamethoxymethylmelamines and methylolacrylamides;

(12) A non-adhesive carboxylated latex product according to (1) to (7), wherein the carboxyl-group blocking agent includes at least one compound selected from glyoxals, polyamide compounds, polyamide polyurea compounds, polyamine polyurea compounds, polyamideamine polyurea compounds, polyamide polyurea glyoxal reaction products, polyamideamine compounds, polyamideamine epihalohydrine condensation reaction products, polyamideamine formaldehyde condensation reaction products, polyamine epihalohydrine condensation reaction products, polyamine formaldehyde condensation reaction products, polyamide polyurea epihalohydrine condensation reaction products, polyamide polyurea formaldehyde condensation reaction products, polyamine polyurea epihalohydrine condensation reaction products, polyamine polyurea formaldehyde condensation reaction products, polyamideamine polyurea epihalohydrine condensation reaction products, and polyamideamine polyurea formaldehyde condensation reaction products,—;

(13) A non-adhesive carboxylated latex product according to (1) to (7), wherein the carboxyl-group blocking agent includes at least one compound selected from monofunctional amines, monofunctional epoxy compounds, monofunctional isocyanates and monofunctional blocked isocyanates;

(14) A non-adhesive carboxylated latex product according to (1) to (7), wherein the carboxyl-group blocking agent is a sizing agent;

(15) A non-adhesive carboxylated latex product according to (1) to (7), wherein the carboxyl-group blocking agent is a non-adhesion surfactant;

(16) A method for producing a non-adhesive carboxylated latex product according to (1) to (15), wherein one or both surfaces of the latex product are brought into contact with one or more of the carboxyl-group blocking agent solutions described in (8) to (15) to attach the carboxyl-group blocking agent to the latex surface;

(17) A method for producing a non-adhesive carboxylated latex ~~dip~~dipped product, characterized in that there is used a solution of a mono- or bi-valent external coagulant for carboxylated latex which is mixed with or dissolved in one or more of the carboxyl group blocking agents described in (8) to (15);

(18) A method for producing a non-adhesive carboxylated latex ~~dip~~dipped product, characterized in that a dipping former is dipped and deposited with one or

more of the carboxyl-group blocking agent described in (8) to (15), dipped and deposited with a mono- or bi-valent external coagulant, and then dipped in a latex;₂

(19) A method for producing a non-adhesive carboxylated latex ~~dip~~dipped product, characterized in that a dipping former is dipped and deposited with one or more of the carboxyl-group blocking agents described (8) to (15), then dipped in a latex liquid to form a latex film, further dipped in a mono- or bi-valent external coagulant solution, and subsequently dipped in the carboxylated latex again;₂

(20) A method for producing a non-adhesive carboxylated latex ~~dip~~dipped product, characterized in that a dipping former is dipped in a mixture of one or more of the carboxyl-group blocking agents described in (8) to (15) and a carboxylated latex stable to the blocking agent to form a latex film, further dipped in a mono- or bi-valent external coagulant solution, and₂ thereafter₂ dipped in the carboxylated latex again;₂

(21) A method for producing a non-adhesive carboxylated latex ~~dip~~dipped product, characterized in that a dipping former is dipped in a mono- or bi-valent coagulant suspension for carboxylated latex which contains, as the carrier, fine powder of one or more of the carboxyl group blocking agents described in (8) to (15) that is hardly soluble or insoluble in water or alcohol, and subsequently dipped in the carboxylated latex liquid;₂

(22) A non-adhesive fingerstall, wherein the fingerstall described in (7) has a shape mechanically wound from the mouth before being removed from the dipping former;₂

(23) A non-adhesive fingerstall according to (7) or (22) which has a ~~wound mouth~~rolled lip;

(24) A method for producing a non-adhesive fingerstall with ~~wound mouth~~a rolled lip according to (23), characterized in that an adhesive portion is provided on the upper part at the time of dipping and then ~~winding is conducted~~wound; and

(25) A method for producing a non-adhesive fingerstall according to (7) or (22), characterized in that the outside surface is treated with a carboxyl group blocking agent after a ~~wound mouth~~rolled lip is provided.

The term carboxyl group blocking agent as used herein means a substance which blocks a carboxyl group chemically, physico-chemically or physically and inhibits the formation of a hydrogen bond derived from the carboxyl group.

Specifically, it means a compound, which can make the carboxylated latex non-adhesive in the adhesion test 1 or 2 of the examples. Further, the non-adhesion surfactant refers to a surfactant, which can make the carboxylated latex non-adhesive in the adhesion test 1 or 2-2 of the examples.

[Brief Description of the Drawings]

Fig.1 is a perspective view of the dipping former transferring apparatus used in the examples. 1, There is shown a chain; 2, 1, a guide rail; 3, 2, a dipping former; 4, 3, a rod; 4, and 5, a guide— 5.

Fig.2 shows the trial apparatus for manufacturing the fingerstall used in the examples. 6, There is shown a dipping tank; 7, 6, a drying furnace; 8, 7, a winding machine; 8, and 9, an unwinding machine— 9.

Fig.3 shows the main parts of the winding machine. 10, There is shown a rolling brush; 10 and 11, a film— 11.

Fig.4 shows the main parts of the unwinding machine.

[Best Mode for Carrying out the Invention]

Detailed Description

The present invention is described in more detail hereinafter.

The first non-adhesive carboxylated latex product of the invention is a latex product in which a non-adhesiveness properties adhesive property have been afforded to it by directly adding a carboxyl group blocking agent into an emulsion latex.

The second is a carboxylated latex product having a treatment layer of the carboxyl group blocking agent on one or both surfaces of the carboxylated latex base. Both products are ~~intrinsically~~ intrinsically non-adhesive. If special use characteristics such as dry or wet wearing ~~properties~~ conditions are required, an outer polymer bonded layer can be provided further on the outside surface according to known technology. ~~The latex~~ Latex products which ~~need prevention against adhesion~~ require a non-adhesive treatment include, but are not limited to, ~~dip~~ dipped products such as balloons, gloves, fingerstalls and condoms, extruded products such as rubber threads and rubber pipes, cast-molded products such as balloons and toys, and whole rubber products or products having rubber surface such as rubber sheets, hoses and draw clothes.

The kind of ~~the~~ carboxylated latex used herein is not limited, but among elastomer latexes of NBR, SBR, CR, MBR and the like, the ones subjected to carboxylation are preferable.

There is no limitation ~~about a so-called~~ as to the vulcanizing agent to be added to the carboxylated latex, ~~and normal~~. Regular vulcanizing agents can be used: e.g., agents for sulfur, peroxide, zinc oxide or radiation vulcanization. However, when the latex product is used in ~~the~~ a field where the reaction of a metal and sulfur is undesirable, for example in the field of precision ~~instrument~~ instruments, sulfur cannot be used as a vulcanizing agent. For such use ~~the~~ a product vulcanized by zinc oxide is generally used, but there is a risk that it may break during wear because of ion crosslinking. Especially for thin gloves or fingerstalls, high durability is required. By adding an internally added aluminum type inorganic crosslinking agent into the carboxylated latex, durability is greatly improved. ~~At the same time, the~~ The range of compounds that can function as carboxyl group blocking agent ~~becomes~~ agents can sharply ~~wide and~~ increase, while the amount to be added can sharply ~~be decreased~~ decrease. Here, the internally added aluminum type inorganic crosslinking agent refers to an inorganic aluminum compound which ~~de~~ does not coagulate the latex at ordinary ~~temperature~~ temperatures even when directly added to the carboxylated latex and which crosslinks the carboxylated latex when heated. The typical examples ~~thereof~~ are alkali metal aluminates such as water-soluble sodium aluminate, alkaline earth metal aluminates such as sparingly soluble calcium aluminate, and aluminum hydroxide gel.

Also included are the groups of various aluminum compounds such as magnesium aluminate metasilicate, synthetic hydrotalcite, aluminosilicagel and aluminosilicate. In other words, they are compounds, which do not dissociate into aluminum ion when added, but combine with a carboxyl group of the latex through ionic crosslink when heated. The aluminum-ion crosslink of these compounds is considered to occur via aluminum hydroxide.

When the latex product is a ~~dip~~ dipped product, it is preferable to use an external coagulant, and any of the usually used external ~~coagulant~~ coagulants can be employed. Usually, mono- or bi-valent metal salts are used, and the monovalent salts include ammonium salts. Here, the external coagulant means one that is not directly

incorporated into the latex but used in the coagulation- dipping process including ~~deposited~~deposition on the dipping former.

The carboxyl group blocking agent used in the invention is a compound which acts on a carboxyl group of the carboxylated latex chemically, physico-chemically or physically, thereby resulting in hydrophobicity which inhibits the formation of a hydrogen bond derived from the carboxyl group so as to make the latex product non-adhesive.

The first carboxyl group blocking agent is a tri-or more valent metal compound. Although any agent can be used if it has three or more valences, it is necessary to fully consider safety issues and side ~~effect~~effects (discoloration) associated with the use of the compound.

~~The example of the tri~~ Tri- or more valent metal ~~compound~~compounds usable as the external crosslinking agent in the invention ~~includes one~~include ones which ~~is~~are soluble in water or alcohol and ~~one~~ones which ~~is~~are sparingly soluble or insoluble. The soluble trivalent metal ~~compound~~compounds include aluminum salts, ferric salts, chromate and thorium salts.—~~Practically,~~ Particularly suitable are aluminum salts such as aluminum chloride, aluminum nitrate, aluminum sulfate and aluminum acetate.

Polyaluminumchloride(PAC) and water-soluble polyaluminum hydroxide are ~~more~~ preferable because they have three or more valences. ~~Especially, water~~ Water-soluble polyaluminumhydroxide ~~gives the~~produces a non-adhesive effect at its ~~low concentration~~concentrations comparable to that of the organic crosslinking ~~agent~~agents, as shown in the examples. If the metal is an amphoteric element, its metal acid salt is usable—and, sodium aluminate ~~is~~being a typical example. ~~Observation suggests~~Observations suggest that sodium aluminate is converted into aluminum hydroxide on the film latex surface and ~~then~~ causes crosslinking.

~~The metal compound~~ Metal compounds, sparingly soluble or insoluble in water or alcohol, that ~~aets~~act as the external crosslinking agent ~~includes~~include oxides, hydroxides and alkaline earth metal salts. ~~The typical~~ Typical examples ~~are~~include aluminum hydroxide, calcium aluminate and magnesium aluminate. The aluminum ~~compound~~compounds include various substances such as aluminosilicates, which fall ~~into~~within the scope of the invention. The usual crystalline aluminum hydroxide is hardly involved in the crosslinking reaction. The so-called amorphous

aluminum hydroxide, when dispersed with a ball mill and made to have a large specific surface, is involved in the crosslinking reaction, and is absorbed on the latex film surface formed. Further, calcium aluminate and magnesium aluminate are absorbed on the latex surface in the same way.

As used herein, the external crosslinking agent refers to ~~the~~ one that is not directly incorporated into the ~~based~~base emulsion latex and crosslinks the latex by ~~contacting its contact~~ with the surface of the emulsion latex or latex film.

The tetravalent metal ~~compound~~compounds used in the invention ~~includes~~include zirconium compounds such as zirconyl nitrate, ammonium zirconyl carbonate zirconyl carbonate W, ammonium carbonate zirconium oxychloride, and titanium compounds such as titanium lactate, titanium maleic anhydride and titanium oxalate.

In the case of a tri- or more valent water soluble metal salt, the dissociated metal ion is cationic and reacts with the anion of carboxyl group even at low ~~temperature~~temperatures. Further, according to the Shultz-Hardy Law, it has a strong crosslinking force. Because of this, the ~~diffusion~~diffusion of the metal ion having three or more valences is very weak, and the reduction ~~of~~in strength of the latex film is ~~minimumized~~minimized. Accordingly, the quality of the final product ~~is kept favorable~~remains good, even if the concentration of the metal salt is considerably high.

The tri- or more valent metal compounds used in the invention include organic compounds. ~~The typical~~Typical examples ~~are~~include carboxylic acid salts, ~~respectively~~such as the above-mentioned aluminum acetate, zirconium acetate, titanium lactate, titanium maleic anhydride, titanium oxalate and titanium lactate. ~~They~~Useful organic compounds are not limited to carboxylic acid salts.

The concentration of ~~the~~ tri- or more valent metal external crosslinking agent ~~agents~~ varies depending on the kind of latex used, the amount of functional groups involved in the reaction, the kind and quantity of ~~an~~ emulsifier or dispersant, the kind of a crosslinking agent, a treatment method, and the crosslinking agent ~~supporting's~~ ability ~~of~~to coat the dipping former. Preferably, ~~it~~the concentration is in the range of 0.1 to 5% (~~as of~~ metal oxide corresponding to the metal element). When the agent is used by ~~incorporation~~incorporating it into the external coagulant, it exhibits a sufficient effect ~~in~~at the range concentration of 0.01 to 0.5%. ~~In the case of working it cases where it is~~

coated on the formed latex film and in the ~~case of providing cases where~~ the external coagulant layer is coated on the external crosslinking agent layer, a preferable concentration is 0.2 to 1%. When the agent is used ~~through incorporation by incorporating it~~ into the external coagulant, it replaces monovalent cations of the latex, usually ammonium ion, potassium ion and sodium ion, to form a crosslink, ~~whereas one other than the above is used as a coagulant and necessary to be replaced with a~~. When a coagulant having bivalent cations is used, the agent replaces the bivalent cation, usually calcium ion, ~~bonded to bond~~ to the latex to form a crosslink.

In ~~the~~ system in which the internally added aluminum type inorganic ~~crosslinking~~ crosslinking agent is directly added to the latex, the concentration of the external crosslinking agent can be decreased.

The second carboxyl group blocking agent is an organic crosslinking agent for the carboxyl group of the carboxylated emulsion latex. Any ~~kind of~~ organic crosslinking agent is usable as long as it is ~~an organic crosslinking agent~~ capable of crosslinking a carboxyl group. ~~The typical Exemplary organic crosslinking agent usually used includes agents include,~~ but are not limited to, aziridine compound, epoxy compound, blocked isocyanate, oxazoline compound, carboimide compound, melamineformaldehyde resin, ureaformaldehyde resin, isocyanate, phenolformaldehyde resin, glycol, polyol, diamine, polyamine, hexamethoxymethylmelamine and metholacrylamide. (~~see~~ See Newest Applied Technology of Latex Emulsion, page 323, Motoharu Okikura (ed) published by Chunichisha, Japan.)

The organic crosslinking agent for the carboxyl group reacts at a considerably high temperature. ~~However, according~~ According to the invention, since ~~its~~ the amount used is very small, it shows ~~the~~ an effect at a temperature of about 90 to 120°C. However, if sufficient time lapses ~~on the stage of~~ at a low temperature, the crosslinking agent diffuses in the Z-axis direction ~~before strength of the latex film is expressed,~~ and competes with the ~~so-called~~ latex vulcanizer, such as zinc oxide, to restrain vulcanization, resulting in ~~lowering the~~ a decrease in film strength. Particularly, the temperature ~~of~~ at the leaching stage of a dipping method is preferably 65 °C or more, ~~more preferably for example~~ 70°C to 85 °C. ~~The temperature~~ Temperatures of 85 °C or more ~~is~~ are not preferable because bubbles ~~are~~ can be generated between the dipping

former and the film. When the concentration of ~~the~~ organic crosslinking agent in the coagulant is high, diffusion of the crosslinking agent becomes ~~large~~greater and the strength is lowered. But, an emulsion type crosslinking agent or highly reactive crosslinking agent diffuses weakly, and the degree of the diffusion also differs depending on the solubility of the crosslinking agent in the coagulant solution. Therefore, it is preferable to determine optimal conditions through an adhesion test. ~~An almost~~A suitable concentration can be determined by carrying out the test at two levels of effective ingredient concentration, 0.025% and 0.0025%. The amount of a crosslinking agent needed to make the carboxylated emulsion latex product non-adhesive is extremely small.

Organic compounds, which do not ~~belong to the~~act as crosslinking ~~agent~~agents for the carboxyl group but are thought to react with a carboxyl group, also have ~~the~~a similar effect. ~~As such~~Examples of effective compounds ~~are~~include the following: glyoxal, polyamide compound, polyamidepolyurea compound, polyamidepolyureaglyoxal condensation reaction product, polyaminepolyurea compound, polyamideaminepolyurea compound, polyamideamine compound, polyamideamineepihalohydrine condensation reaction product, polyamideamineformaldehyde condensation product, polyamineepihalohydrine condensation reaction product, polyamineformaldehyde condensation reaction product, polyamidepolyureaepihalohydrine condensation reaction product, polyamidepolyureaformaldehyde condensation reaction product, polyaminepolyureaepihalohydrine condensation reaction product, polyaminepolyureaformaldehyde condensation reaction product, polyamideaminepolyureaepihalohydrine condensation reaction product, and polyamideaminepolyureaformaldehyde condensation reaction product.

Many of these compounds were developed as ~~waterproof-endowing agent~~waterproofing agents, printability improver, wet strength improver, paper strength reinforcing agent ~~effor~~for papers, ~~and they are common in that they~~. They were developed as chemicals to inhibit the formation of hydrogen bonds in paper. ~~The reaction~~Reaction conditions and ~~the~~ concentration of the compounds ~~are~~ similar to those of the organic crosslinking agent, ~~providing~~provide comparable ~~effects~~results.

The methods of producing the above-mentioned compounds are not limited, ~~but to~~ the general methods ~~are~~ described hereinafter.

The polyamide compound (also called polyamideamine compound) is obtained by dehydration condensation reaction of a polyamine and a compound having carboxyl group. The polyamidopolyurea, polyaminopolyurea, polyamideaminopolyurea and polyamideamine compounds are reaction products ~~between~~from polyalkylenepolyamine or alkylenepolyamine, urea, and dibasic carboxylic acid. The compounds can be modified with a small amount of aldehyde, epihalohydrine or α,γ -dihalo- β -hydride. The method of their production is described in Japanese Patent Publication (Kokoku) No.59-32597 and Japanese Patent Application Laid-Open (Kokai) No.4-10097.

The polyamideamine-epihalohydrine condensation reaction product, polyamideamine-formaldehyde condensation reaction product, polyamine-epihalohydrine condensation reaction product, polyamine-formaldehyde condensation reaction product, polyamidopolyurea-epihalohydrine condensation reaction product, polyamidopolyurea-formaldehyde condensation reaction product, polyaminopolyurea-epihalohydrine condensation reaction product, polyaminopolyurea-formaldehyde condensation reaction product, polyamideaminopolyurea-epihalohydrine condensation reaction product and polyamideaminopolyurea-formaldehyde condensation reaction product, are reaction products ~~between~~from polyalkylenepolyamine, urea, dibasic carboxylic acid, and epihalohydrine or formaldehyde. The ~~manufacture~~manufacturing methods are described in Japanese Patent Publication (Kokoku) No.52-22982, Japanese Patent Publication (Kokoku) No.60-31948, Japanese Patent Publication (Kokoku) No.61-39435 and Japanese Patent Application Laid-Open (Kokai) No.55-127423.

~~The~~ A sizing agent for paper is a chemical, which makes the hydrophilic group of paper hydrophobic and prevents ~~the soak of ink, and also such chemical~~ it from soaking up ink. This chemical also makes the carboxylated latex product non-adhesive. It is ~~considered~~contemplated that the chemical makes the carboxyl group hydrophobic chemically, physico-chemically or physically. There is no established theory for the hydrophobicity-forming mechanism, but the sizing agent gives a large and stable effect since it has been developed as a sizing agent of paper.

~~The sizing agent~~ Sizing agents for paper ~~includes~~include internally added sizing agents and surface sizing agents. The invention can use any sizing agent on ~~the like~~ as long as it ~~exhibit the function~~exhibits the ability to create a non-adhesive surface.

~~The internally~~ Internally added sizing agent ~~is~~can be classified ~~into~~as an acid sizing agent, a neutral sizing agent and an acid/neutral sizing agent (Japanese Patent Application Laid-Open (Kokai) No.11-61682).

~~The~~ An acid sizing agent ~~includes~~can include rosin sizing agent, fatty acid soap sizing agent, synthetic sizing agent and petroleum resin sizing agent.

~~The rosin~~ Rosin sizing agent ~~includes~~agents include rosins and rosin derivatives. The rosins refer to gum rosins, wood rosins and ~~to~~tall oil rosins which contain, as the main component, resin acids such as abietinic acid, palustric acid, neoabietinic acid, pimaric acid, isopimaric acid and dehydroabietinic acid.

~~The rosin~~ Rosin derivatives include hydrogenated rosins, polymerized rosins, modified rosins, fortified rosins, rosin esters and fortified rosin esters.

~~The modified~~ Modified rosins include (alkyl)phenol-formalin resin modified rosins, xylene resin modified rosins, aldehyde modified rosins and styrene modified rosins.

~~The fortified~~ Fortified rosins are obtained by heating and reacting the ~~said~~ rosins and α , β -unsaturated carboxylic acids.

~~The rosin~~ Rosin esters are produced using rosins and polyhydric alcohols by ~~the~~ known esterification.

~~The fortified~~ Fortified rosins are obtained by successively or simultaneously reacting the ~~said~~ rosins and/or the ~~said~~ modified rosins with known polyhydric alcohols and α , β -unsaturated carboxylic acids.

~~The fatty~~ Fatty acid soap sizing agent is a sizing agent obtained by neutralizing a fatty acid having ~~the carbon number of~~ about 8 to 24 carbons such as palmitic acid or stearic acid and a mixture thereof with an alkali.

~~The~~ A synthetic sizing agent includes ~~the~~ a sizing agent obtained by neutralizing with an alkali a substituted succinic anhydride obtained by reacting an oligomer, dimer or tetramer, of isobutene and a mixture thereof with maleic anhydride.

~~The~~ A petroleum resin sizing agent includes one obtained by modifying a petroleum resin with an unsaturated carboxylic acid such as maleic acid. The petroleum resin

~~includes~~can be C5 petroleum resin obtained by polymerizing C5 olefin such as 1,3-pentadiene or isoprene, C9 type petroleum resin obtained by polymerizing C9 olefin such as coumarone or indene, C5/C9 copolymer type petroleum resin obtained by copolymerizing C5 olefin and C9 olefin, and dicyclopentadiene type petroleum resin obtained by polymerizing dicyclopentadiene or its derivative.

~~The neutral~~ Neutral sizing agent ~~includes~~agents include alkylketenedimer type, alkenylketenedimer type, alkenyl succinic anhydride type and neutral rosin type sizing agents.

~~The~~ Usually, an alkylketenedimer type or alkenylketenedimer type sizing agent can be ~~usually~~ produced by emulsifying an alkylketene dimer or alkenylketene dimer which is prepared by treating a saturated or unsaturated fatty acid chloride having ~~the carbon number of about 12 to 24~~ carbons with a base such as triethylamine to make a dimer. The alkenyl succinic anhydride type sizing agent can be prepared by emulsifying an alkenyl succinic anhydride obtained by ~~the addition reaction~~ of a terminal and /or internal olefin having ~~the carbon number of about 12 to 24~~ carbons with maleic anhydride.

~~The neutral~~ Neutral rosin sizing agent ~~includes~~agents include polyhydric alcohol esters of rosins, and emulsions made by dispersing petroleum resin-containing substances in water.

~~The polyhydric~~ Polyhydric alcohol esters of ~~said~~the rosins include reaction products containing rosin esters obtained by reacting rosins, with (a) at least one chemical belonging to the ~~scope~~family of polyhydric alcohols and (b) at least one chemical belonging to the ~~scope~~family of α , β -unsaturated carboxylic acid or its derivative.

~~As the acid~~ Acid/neutral sizing agent ~~there are known~~agents include cationized fatty acid bisamide type, cationized petroleum resin type, cationized polymer type and α -hydroxycarboxylic acid type sizing agent.

~~The cationized~~ Cationized fatty acid bisamide type and cationized petroleum resin type sizing agent ~~agents~~ are synthesized by reacting a maleic acid adduct of a fatty acid having about 12 to 24 carbons or a petroleum resin with a polyamine such as diethylenetriamine and triethylenetetramine and a mixture thereof, followed by a reaction with epichlorohydrine.

The cationic polymer type sizing agent is usually synthesized by ~~radical~~radically polymerizing a cationic vinyl monomer, such as dimethylaminoethylmethacrylate, and a hydrophobic monomer, such as styrene, acrylonitrile or alkyl(meth)acrylate, in water and /or in an organic solvent.

The α -hydroxycarboxylic acid type sizing agent is made by reacting a higher alcohol or higher amine with an oxyacid such as citric acid.

~~The surface~~ Surface sizing ~~agent~~agents generally ~~comprises~~comprise a hydrophobic portion and an anionic portion such as a carboxyl group. The surface sizing agent is obtained by copolymerizing a hydrophobic monomer and an anionic monomer such as α , β -unsaturated monocarboxylic acid, α , β -unsaturated dicarboxylic acid and unsaturated sulfonic acid. (~~see~~See Japanese Patent Application Laying-Open (kokai) No.12-4519745197.)

~~The example~~ Examples of ~~the surface sizing agent~~agents which ~~consists~~consist of a copolymer of a hydrophobic monomer and an anionic monomer ~~includes~~include styrene-(meth)acrylic acid copolymer, styrene-(meth)acrylic acid-(meth)acrylic acid ester copolymer, styrene-maleic acid copolymer, styrene-maleic acid-maleic acid halfester copolymer, (di)isobutylene-maleic acid copolymer, (di)isobutylene-maleic acid-maleic acid halfester copolymer and salts of these.

~~The surface~~ Surface sizing ~~agent~~agents, other than the above-mentioned ~~includes~~, include alkylketene dimer, alkenyl succinic acid(anhydride), styrene-acrylic acid copolymer, acrylate-acrylonitrile copolymer, styrene-dialkylaminoalkyl(meth)acrylate copolymer, and ~~reaction product thereof~~these products reacted with epihalohydrine.

The carboxyl group blocking agent is not necessarily a crosslinking agent for the carboxyl group. If it is a substance which acts on the carboxyl group chemically ~~or~~, physico-chemically ~~further~~, or physically, ~~which makes~~making the site hydrophobic and ~~hinders~~hindering the formation of a hydrogen bond, the agent makes the carboxylated latex product non-adhesive.

~~Conerately~~ Consequently, even the compounds that cannot form crosslinking ~~structures~~structures with the carboxyl ~~group~~groups, for example, monofunctional amines, monofunctional epoxy compounds, monofunctional isocyanates and monofunctional blocked isocyanates, can make the carboxylated emulsion latex product non-adhesive.

~~Since~~Because they have only one functional group, crosslinking does not occur. However, if these compounds have hydrophobic ~~group~~groups, they react with a carboxyl ~~group~~groups to result in hydrophobicity.

As ~~to~~for the amines, any ~~of~~ primary, secondary, tertiary ~~and quaternary amines~~ gives the or quaternary amine can provide this effect.

The A surfactant is composed of hydrophilic group and hydrophobic group. If the hydrophilic group is arranged ~~to~~towards the surface of the carboxylated emulsion latex product and the hydrophobic group ~~to~~away from the ~~outside~~surface, supposedly the carboxyl group of the product surface is blocked ~~to form~~, resulting in hydrophobicity and ~~to make~~making the surface non-adhesive. Accordingly, it is ~~supposed~~thought that the degree of hydrophobicity of the surfactant controls the degree of non-adhesion of the product. Whether the surfactant takes up the position on the product surface with the hydrophobic group directed to the outside is determined by the physical and chemical properties of the surfactant itself, the properties of the latex, addition or ~~no~~ addition~~absence~~ of aluminum compounds and the like. ~~And it~~It is difficult to find a general rule. ~~So~~Therefore, it is necessary to select non-adhesion ~~surfactants~~surfactants through the adhesion test 2 shown in the examples. The results of the test were that the surfactant showed ~~the~~a non-adhesion effect in ~~the case that the internal addition-uses~~situations where the internally added aluminum type inorganic crosslinking agent such as aluminum hydroxide gel and aluminate, was added ~~into~~to the emulsion latex. ~~The presumable reason for this is that~~Presumably, the surfactant, viewed in ~~the~~ light of its properties, diffuses throughout the latex film. The ~~internal addition-use~~internally added aluminum type inorganic crosslinking agent is thought to suppress diffusion of the surfactant.

Regarding With respect to the nonionic surfactant, a general ~~tendency~~rule cannot be found. However, it ~~is seen~~can be said that ~~the~~a nonionic surfactant having a high HLB shows a ~~lowered~~low non-adhesion effect and that ~~the~~a nonionic surfactant of amine and amide types shows a high non-adhesion effect.

~~In the~~ With cationic ~~surfactants~~surfactants and the amphoteric ~~surfactants~~surfactants, the ~~cation~~cations of the surfactant and the ~~anion~~anions of the carboxyl group combine ~~with~~to form an ion linkage. Hence, many of these give good results when subjected to the above-mentioned adhesion test. However, since ~~the both~~ surfactants ~~make chemical~~

~~reaction~~react chemically with carboxyl ~~group~~groups at low temperatures, they influence the formation of the latex film in the dipping step; if they are added ~~into~~ the coagulant ~~for use~~. That is, ~~according to~~depending on the ~~kind~~type and concentration of the surfactant, fine wrinkles ~~are~~can be generated toward the direction of the dipping, and sometimes cracks ~~are~~can be generated. Further, if the surfactant diffuses internally into the ~~inside~~film, it competes with the so-called latex vulcanizing agent, such as zinc oxide, and hinders vulcanization to cause a decrease of the strength of the film. Consequently, countermeasures are needed ~~of restraining for keeping~~ the surfactant concentration low to suppress diffusion, accelerating vulcanization by raising the temperature of the drying and leaching process and so forth. ~~However, and~~ these are big drawbacks to the manufacturing process. From the above-mentioned point ~~the~~, an adhesion test is needed to select the appropriate surfactant and its concentration.

It is unclear how ~~the~~an anionic surfactant ~~gives~~provides the non-adhesion~~adhesive~~ effect. Generally, ~~the~~an anionic surfactant is used as an emulsifier in synthesizing the carboxylated emulsion latex. Moreover, dodecylbenzenesulfonic acid, for example, reacts with metal salts in the coagulant ~~at the~~during dipping, converting most of it ~~being converted to~~ metal soap, and it ~~loses the~~losing its ability to function as a surfactant. Metal soaps, as seen from the fact that they are used as lubricating oil, have more or less adhesion. But, ~~among the~~some anionic surfactants ~~some show~~produce excellent non-adhesion~~effect~~adhesive effects. There are many effective surfactants among those that have amine and amide group in the structure and are considered to react with the carboxyl group and those that have a polycyclic structure and are considered to be highly hydrophobic. For example, the use of naphthalenesulfonic acid formaline condensation reaction products or alkylnaphthalenesulfonic acid formaline condensation reaction products is effective for producing a non-adhesive latex product. The above-mentioned rosin sizing agent ~~is interpreted to belong to~~falls into this category.

~~The surfactant~~ Surfactants, because of ~~its~~their properties, ~~has~~have a great effect on each manufacturing step of the carboxylated emulsion latex product and on the properties of the product. Therefore, in order to judge whether a surfactant is usable or not, it is necessary to confirm ~~the~~its ability to have a non-adhesion~~adhesive~~ effect by conducting

the adhesion test and, at the same time to study, studying the effect on the film ~~forming~~formed and its quality.

There are a variety of methods for manufacturing the non-adhesion adhesive latex product of the invention.

When the product has already been formed into a film, it is possible to bring one surface or both surfaces of the product in contact with the carboxyl group blocking agent solution and to treat the carboxylated latex surface with the ~~said~~ blocking agent. ~~According to~~ Depending on the kind of the carboxyl group blocking agent, the reaction ~~is~~ can be very fast, and ~~at~~ by the time ~~when the product is taken out of the solution,~~ sometimes the latex film surface ~~has~~ may have already lost its adhesiveness. ~~But sometimes~~ In other situations, heating is needed after the product has been taken out of the solution. Either way, to obtain the full effect of the treatment ~~effect fully,~~ it is desirable to conduct ~~heat treatment~~ a heating step.

In the case of a ~~dip~~ dipped product, by depositing one or more carboxyl group blocking agents and ~~a~~ an usual external coagulant onto the dipping former and then bringing it into contact with the emulsion latex, coagulation of the latex and treatment with the blocking agent can be conducted at the same time.

There are four methods for depositing the carboxyl-group blocking agent on the dipping former. The first method is one wherein ~~a usual~~ an external coagulant consisting of mono- or bi-valent metal ~~salts~~ salts and one or more of the carboxyl group blocking agent of the invention are mixed ~~and~~ dissolved, and deposited onto the dipping former. The second method is one wherein the carboxyl-group blocking agent of the invention is deposited onto the dipping former and, thereafter ~~a usual~~ an external coagulant is deposited onto the formed layer. Modifying this method gives a method wherein the carboxyl group blocking agent is incorporated into the emulsion carboxylated latex, the dipping former is dipped in said formulation liquid to form a thin latex film, the former is dipped in a mono- or bivalent external coagulation solution, and then the former is dipped in the carboxylated latex solution again.

The third method is one wherein one or more of the powdery carboxyl blocking agents of the invention is used as a support, ~~said~~ The carboxyl group blocking agent ~~being~~ is suspended in ~~a usual~~ an external coagulant solution, and then deposited onto the dipping former. This method does not give a perfect non-powder product, but,

since the carboxyl-group blocking agent reacts with the latex and is absorbed, the powder can be reduced to such a degree as to be unable to be perceived on the finished product.

By immersing such dipping former in the emulsion latex, there is obtained a ~~dipped~~ product in which the inside surface contacting the former is non-adhesive.

The fourth method is one wherein a thin, carboxyl group blocking agent treated film of the latex is formed by using the carboxyl group blocking agent as an external coagulant, the external coagulant consisting of a mono- or bi-valent metal compound is deposited onto the film, and the former is dipped in the latex liquid again. With this method it is possible to make the inside surface non-adhesive, but it is feared that peeling may occur between the layers of the product.

Further, the outside ~~surfaces~~surfaces can be made non-adhesive by the above-mentioned methods.

In the case of cast-mold products, the inside surface of the mold is treated only with the carboxyl group blocking agent of the invention.

As mentioned above, it is possible, by using the present invention to fabricate ~~the~~ latex product non-adhesive in one or both surfaces. The ~~surfaces~~surfaces of such products ~~does do~~ not ~~attach~~adhere together when each surface comes into contact with the other under heating during and after the manufacturing ~~them~~process.

Accordingly, by utilizing ~~such a~~this property, a product can be produced that has never existed until now.

One ~~of such products~~product is a non-adhesive fingerstall mechanically wound (rolled) from its mouth before ~~removing~~being removed from the dipping former. ~~The fingerstall~~Fingerstalls wound from the mouth ~~has been existed until now, are known~~ and ~~its~~their usefulness ~~has~~have been recognized because of ~~its easy to wear~~their ease in use. However, ~~the~~ both surfaces of ~~the~~ fingerstall, a latex product, are intrinsically adhesive; and in In order to manufacture the wound product, the fingerstall ~~is~~had previously been made non-adhesive by ~~a treatment~~treatments such as powdering and post-chlorination, followed by winding with human hands. This makes it impossible to maintain the high ~~cleanness~~degree of cleanliness of the product ~~and it is difficult to use the conventional fingerstall in a workplace~~needed for its use in workplaces where precisely processed articles are manufactured, such as in clean rooms. The present invention, however,

which is able to make ~~the~~ both surfaces of the latex molding non-adhesive, ~~can afford to~~ mechanically wind allows for mechanical winding of the fingerstall on the dipping former and can therefore maintain ~~the~~ a high cleanliness degree of cleanliness of the product.

Recently, ~~a thin fingerstall is~~ fingerstalls are desired since wearing ~~a thick one~~ tends ones tend to cause ~~tiredness~~ exhaustion. The thinner the fingerstall, however, the more difficult ~~to wear it, so it is to use~~. Accordingly, what is desired is a wound fingerstall that is easy to use, thin, powder-free, non-adhesive and clean.

By utilizing the property that ~~the~~ both surfaces of the fingerstall are non-adhesive, fingerstalls ~~with wound~~ at the mouth can easily be manufactured. In manufacturing the fingerstall, the top of the stall is left adhesive without providing the layer of the carboxyl group blocking agent, the whole ~~is~~ can be wound up, and then unwound. The portion having adhesion remains as a ~~wound mouth~~ rolled lip. Hitherto, the ~~wound mouth has~~ rolled lip had been formed first by winding up only the top of the stall to make the ~~wound mouth~~ rolled lip, and, thereafter, the stall ~~has been~~ had to be released from the former in another step. The ~~wound mouth~~ rolled lip facilitates wearing and removal doffing of the stall and is highly ~~desired~~ desirable for flat products. Further, after formation of the ~~wound mouth~~ rolled lip according to the prior art, non-adhesion treatment can be conducted to achieve the objective.

~~Further, the wound mouth can be provided for the wound fingerstall mentioned in the previous paragraph.~~

{Example}

The present invention is explained in detail using examples hereinafter, but the invention is not limited to the examples. The ~~percentage~~ percentages and ~~the~~ amounts per part shown in the examples are ~~a~~ percentages by weight ~~percentage~~ and ~~a weight~~ parts unless otherwise indicated. Further, in the examples mentioned below, unless otherwise ~~shown~~ indicated, the latex film was prepared by the dipping method ~~from because of the viewpoint~~ ease of ~~easiness of~~ conducting the experiments and ~~easiness of~~ ease in confirming the effect. The present invention, however, is not limited to ~~the dipping products~~ and methods of manufacturing dipped products.

(Preparation of Latex Film)

Using a test tube-like shaped, glass-made dipping former for making ~~fingerstall~~fingerstalls, a latex film was prepared. When an external coagulant and a carboxyl-group blocking agent of solution types were used, a sand-blasted glass-made dipping former was used. When a powdery carboxyl-blocking agent was used, a transparent glass-made dipping former not subjected to sand blasting was used. First, the dipping former was dipped in the external coagulation liquid, to ~~attach~~coat the ~~liquidformer~~, and dried. Next, the dipping former was dipped in a latex emulsion to form a latex film, ~~and then drying, leaching and dried, leached and subjected to a vulcanization treatment were conducted according to the conventional method~~methods. ~~In the case of treating~~ In cases where the outside surface of the film is to be treated, the dipping former affixed with the film is ~~again~~-dipped in a solution or suspension liquid of the carboxyl group blocking agent, followed by drying and leaching ~~treatment~~steps. ~~As the~~ The latex, used is a carboxylated NBR, NIPOL LX-551, made by Nippon Zeon ~~was used, unless specially mentioned~~otherwise specified. The latex, however, is not limited to this type.

The properties of LX551 are shown below.

Solids	45%
PH	8.5
Viscosity	85 mPs
Gel content	0%
Tg	-14 .
Combined AN content	37%

To 100 parts of the above-mentioned latex, fine zinc ~~flower~~oxide was added as a vulcanizing agent, and the mixture was subjected to the following test.

(Adhesion Test of Latex Film-1)

The adhesion of the latex film is highest when the film is heated in ~~the~~a water-containing state.

After the leaching step, following the non-adhesion treatment of the outside surface in the film manufacturing process, the latex film is wound on the dipping former and removed from the dipping former ~~as it stands~~. This sample is heated in a hot air dryer at 70-°C for 30 minutes, taken out and unwound after cooling. The film is thick

because it is wound, and the sample is always in ~~the~~ wet condition during the test. Accordingly, if ~~the~~ both surfaces of the film are non-adhesive, unwinding is easy, ~~and~~ if it is adhesive, unwinding is difficult.

Comparative Example 1

(Preparation of External Coagulation Solution)

A solution of calcium nitrate tetrahydrate 150g and water or methanol 1000g was prepared to make an external coagulant (hereinafter called coagulant 1).

(Manufacture of Latex Film)

A sand-blasted glass pipe is dipped in the aqueous external coagulant 1 and dried. The glass pipe ~~attached~~ coated with the external coagulant is dipped in a latex emulsion to form a latex film. The film affixed on the dipping former is dried softly at 50 °C for 3 minutes and further subjected to the leaching treatment for 3 minutes in ~~the~~ hot water ~~of~~ at 70 °C. Subsequently, the film is wound on the former and released from the former. The film is unwound and subjected to a vulcanization treatment in a hot air dryer at 120 °C for 30 minutes to make samples ~~for testing~~ to test their strength. For the adhesion test, the sample wound and removed from the former was presented as it stood. The sample after the adhesion test could not be unwound. The test results of film strength and adhesion are shown in Table 1.

~~The sample after the adhesion test could not be unwound.~~

(Example 1)

The film formed in Comparative Example 1 is leached, released from the former, unwound, dipped in an aqueous solution of polyaluminumchloride (which is an external crosslinking agent) containing 2.5% as-alumina and immediately taken out. At this time, the film surface already has lost its adhesiveness and ~~gives~~ has a feeling of smoothness. This film ~~is~~, dried at 70 °C for 3 minutes, is further subjected to a leaching treatment in ~~the~~ hot water at 70 °C for 3 minutes, and subjected to a vulcanization treatment in the same manner as Comparative Example 1. The results of the strength test of the film are shown in Table 1. For the adhesion test, the film, which underwent leaching treatment after non-adhesion treatment of the outside surface, was again placed

on the former. The film was wound to make test samples. The sample after the adhesion test could easily be unwound.

(Example 2)

The dipping former was dipped in a solution of polyaluminum chloride (which is an external coagulant) containing 2.5% ~~as~~-alumina and used in Example 1, ~~attached to~~ coat the former, then dried, next dipped in the external coagulant methanol solution ~~1~~, ~~attached~~ 1 and dried. ~~The~~ Then the dipping former was dipped in the latex liquid to form a film, then dried at 50 °C for 3 minutes and further subjected to a leaching treatment at 50 °C for 3 minutes. Thereafter, the former was again dipped in the aqueous solution of polyaluminum chloride used in Example 1 in order to prevent the adhesion of the film's outside surface and subjected to a leaching treatment and a vulcanization treatment. The test results on the film strength are shown in Table 1. The sample, after the adhesion test, was able to be unwound easily. This shows that the inside surface of the film contacting the dipping former ~~has~~ had become non-adhesive. The outside surface is also non-adhesive, as in Example 1.

(Example 3)

~~Except that~~ In this example, aluminum acetate, containing 2.4% ~~as~~-alumina was used in place of polyaluminum chloride ~~which is attached to,~~ was coated on the dipping former ~~and in which the formed film is dipped,~~ by dipping. The latex film was prepared as ~~within~~ Example 2-2 and was dipped with the former. Table 1 shows the test results on the strength of the film. The film wound in the adhesion test could easily be unwound.

(Example 4)

Using aluminum nitrate containing 0.2% alumina and a solution containing calcium nitrate tetrahydrate 150g and methanol 1000g as an external coagulation liquid and external crosslinking liquid, a film was produced. ~~Then, there was conducted~~ Adhesion preventing treatment of the outside surface of the film according to the same ~~operation~~ procedure as in Example 2-2 was performed. The film thickness was approximately equal to that of Comparative Example 1 and Example 2. The test results on the strength of the film are shown in Table 1. In this case too, as with Example 2, the sample after the adhesion test could easily be unwound.

(Comparative Example 2)

The dipping former was dipped in the external crosslinking agent, polyaluminum chloride solution, used in Example 1, and a film was formed in the same manner as Comparative Example 1. The film thickness was only 0.03 mm, and the polyaluminum chloride was found to be unsuitable as an external coagulant. Using various aluminum compounds such as aluminum chloride, aluminum nitrate and aluminum acetate, the same tests as above were conducted. The results were the same.

(Comparative Example 3)

The order of attaching the external crosslinking agent and the external coagulant to the former in Example 2 was ~~inverted~~reversed, and the dipping treatment was conducted so that the layer of polyaluminum chloride ~~might come~~is found on the outside surface. The thickness of the film was only 0.04 mm, being similar to Comparative Example 2. This ~~formulation~~method was unsuitable for external coagulant formulation.

(Reference Example 1)

~~Except that fine zinc flower was not added in the emulsion latex, a~~ A latex film was prepared in the same way as Example 3-3 except that fine zinc oxide was not added in the emulsion latex. As with Example 3, the film formed had at~~the~~ usual thickness, and ~~the~~ both surfaces of the film were non-adhesive. On the other hand, the strength of the film was extremely low. ~~This fact can~~It may be ~~interpreted as~~ that the aluminum crosslinking layers are extremely thin and ~~it does~~they do not contribute to ~~the~~ film strength.

(Comparative Example 4)

~~Except~~ A latex film was prepared in the same way as Example 1 except that an aqueous solution of zinc nitrate containing 5% ~~as~~ zinc oxide was used in place of polyaluminum chloride, ~~a latex film was prepared in the same way as Example 1.~~ The film was adhesive, and it was impossible to ~~carry out unwinding~~unwind the wound finger stall after the adhesion test. Zinc is bivalent and insufficient to make the film non-adhesive.

Table 1 shows the test results on ~~the~~ film strength.

(Example 5)

An aqueous solution of sodium aluminate and an aqueous solution of calcium nitrate were mixed to prepare calcium aluminate. A solution of water/methanol(1/1)

was prepared to make calcium aluminate 20g/1000g (calculated as anhydride) and calcium nitrate tetrahydrate 150g/1000g.

A transparent glass ~~made~~ dipping former was dipped in ~~said~~the external coagulation liquid, ~~a~~A coagulant layer was formed on the former using ~~calcium~~calcium aluminate as a support, ~~and thereafter a~~A latex film was prepared in the same way as Example 2.

On the dipping former calcium aluminate ~~remains~~coated thinly, but when the inside surface, after vulcanization ~~is~~was observed, the calcium aluminate ~~is hardly recognized~~was barely noticeable. The sample, after the adhesion test, could be unwound. The test results of the film strength are shown in Table 1.

When the dipping former is vigorously shaken immediately after the latex film is formed ~~throughby~~ dipping in the emulsion latex, the latex film breaks down. Under the latex layer ~~broken down~~, a very thin aluminum treatment layer is ~~recognized~~present. Taking into consideration this fact and Reference Example 1, it is ~~understandable~~evident that the aluminum treatment layer is a very thin layer.

(Example 6)

Dry aluminum hydroxide gel made by Tomita Seiyaku Co. was dispersed with a ball mill for 24 hours and then added ~~with~~to water and methanol so that a suspension of aluminum hydroxide 20g (calculated as anhydride) in 1000g water/methanol(1/1) and calcium nitrate tetrahydrate 150g in 1000g water/methanol(1/1) ~~is~~was prepared. Thereafter, a latex film was formed in the same ~~way~~manner as Example 5. The test results on strength are shown in Table 1. The wound film could easily be unwound as with Example 4.

In the process of heating the film, it ~~is~~was observed that aluminum hydroxide is absorbed ~~in~~into the latex film.

(Comparative Example 5)

There was prepared a suspension solution of water/methanol(1/1) having light calcium carbonate 100g/1000g, bentonite 50g/1000g and calcium nitrate tetrahydrate 150g/1000g. A latex film was manufactured in the same ~~way~~manner as Example 5.

The wound latex film could not be unwound even before heating. ~~The~~A sample for testing the strength was prepared using talc as the powder to provide the non-adhesive effect.

(Comparative Example 6)

~~Except~~ A latex film was made in the same manner as Comparative Example 1 except that 1 part of aluminum hydroxide used in Example 6 (calculated as anhydride) was added into 100 parts of a latex, ~~a latex film was made in the same manner as Comparative Example 1.~~ The wound film could not be unwound.

(Example 7)

Using an aqueous solution containing 0.2% aluminum nitrate (as alumina) and 150g calcium nitrate tetrahydrate in 1000g water as the external coagulant and concurrently as the external crosslinking agent, a latex film was fabricated. Thereafter, the outside surface of the film was dipped in an aqueous solution of zirconyl acetate, 1.5% as-ZrO₂, and ~~the leaching and vulcanization treatment~~ vulcanizing treatments were conducted in the same manner as Example 2. The results of the strength test on the film are shown in in Table 1. The sample₂ after the adhesion test₂ could easily be unwound.

(Example 8)

Using an aqueous solution containing 0.2% zirconyl nitrate (as-ZrO₂) and 150g calcium nitrate tetrahydrate in 1000g water as the external coagulant and concurrently as the external crosslinking agent, a latex film was prepared. Thereafter, the outside surface of the latex film was dipped in an aqueous solution of polyaluminum ~~ehloride~~ chloride (2.5% as-alumina), leaching and ~~vulcanization~~ vulcanizing treatments were conducted in the same manner as Example 2. The results of the strength test for the film are shown in Table 1. The sample₂ after the adhesion test₂ could easily be unwound.

(Example 9)

A latex film was prepared in the same manner as Example ~~77~~, except that an aqueous solution of titanium lactate of 1.5% ~~as~~ TiO₂ was used in place of zirconyl acetate. The results of the strength test ~~offor~~ the film are shown in Table 1. The sample₂ after the adhesion test₂ could easily be unwound.

(Example 10)

An adhesion test of ~~thea~~ latex film was conducted in the same ~~way~~ manner as Example ~~44~~, except that carboxylated SBR (SBR 2570X5 made by Nippon Zeon Co.) was used in place of NBR. The sample₂ after the adhesion test₂ could easily be unwound. Zinc oxide was not incorporated ~~ininto~~ SBR in the experiment.

(Example 11)

~~Except~~ A latex film was prepared in the same manner as in Example 5 except that carboxylated CR latex mentioned below was used in place of NBR, ~~a latex film was prepared in the same manner as in Example 5.~~ The results of the strength test for the ~~films~~film are shown in Table 1. The sample, after the adhesion test, could easily be unwound.

Carboxylated CR latex made by Toso Co.

GFL-280 60 parts

LA-502 40 parts

(further containing Zinc ~~flower~~oxide made by Seido Kagakusha Co., 5 parts)

The pH and viscosity of the formulation latex was 8.9 and 37.8 mPs, respectively.

(Comparative Example 7)

A latex film was formed using the carboxylated CR latex used in Example 10 and using calcium nitrate as an external coagulant. The film, thus formed, had strong adhesiveness and was impossible to remove from the dipping former. ~~The~~This latex ~~finds an application~~can be used as an adhesive.

Table 1

	Thickness of film (mm)	Maximum load stress (kgf/cm ²)	Maximum load strain (%)	Adhesion test	Remarks
Example 1	0.11	390	680	Possible to unwind	
Example 2	0.12	370	695	Possible to unwind	
Example 3	0.12	370	680	Possible to unwind	
Example 4	0.12	380	690	Possible to unwind	
Example 5	0.13	480	790	Possible to unwind	
Example 6	0.09	450	720	Possible to unwind	
Example 7	0.11	290	700	Possible to unwind	
Example 8	0.10	300	720	Possible to unwind	
Example 9	0.11	310	680	Possible to unwind	
Example 11	0.12	256	1040	Possible to unwind	
Example 12	0.12	340	732	Possible to unwind	Easy to wear
Example 13	0.11	350	650	Possible to unwind	Very easy to wear
Reference Example 1	0.09	30	640	Possible to unwind	Poor strength
Comparative Example 1	0.12	410	690	Impossible to unwind	
Comparative Example 2	0.03	Not determined	Not determined	Not tested	Defect of film thickness
Comparative Example 3	0.04	Not determined	Not determined	Not tested	Defect of film thickness
Comparative Example 5	0.08	530	750	Impossible to unwind	
Comparative Example 6	0.07	490	760	Impossible to unwind	

(Example 12)

~~There was fabricated a trial equipment~~ An instrument for manufacturing fingerstalls, as shown in Fig.2 ~~which~~2, is equipped with a dipping former transferring apparatus (see Japanese Patent Application Laying-Open (kokai) No.7-329084). Using this ~~equipment~~instrument, fingerstalls were produced in the same manner as Example 2 to Example 6. The dipping former transferring apparatus of Fig. 1 transfers the dipping former 3 with its chain 1 ~~being moved~~, which moves along the guide rail 2.

~~The~~ A rod 4 moves along the guide 5 and enables the dipping former 3 to move upwards and downwards. In Fig. 2, when the dipping former 3 ~~passes through~~ reaches a dipping tank 6, the dipping former 3 is ~~dipped in~~lowered into the dipping tank ~~with its being lowered~~. ~~Each of~~ The external crosslinking solution tank, external coagulation solution tank, latex liquid tank and leaching treatment tank ~~is made ready~~have previously, ~~the~~ been made ready. The tanks are switched ~~where~~when

deemed necessary, and each applicable dipping treatment and leaching treatment ~~are~~is carried out in series. After each dipping treatment and leaching treatment, the dipping former 3 is transferred to ~~the~~a drying furnace 7 and dried. Except when ~~the~~a winding machine 8 and ~~the~~an unwinding machine 9 are used, the dipping former 3 is kept so that it ~~does~~is not ~~come~~brought downwards ~~and kept~~ so that it does not come into contact with the winding machine 8 and the unwinding machine 9. ~~At~~During the ~~time of~~ drying and leaching treatment, the dipping former 3 is stopped ~~to undergo treatment~~ for a ~~predetermined~~sufficient period to undergo the treatments. The winding machine 8 rotates a roll type brush 10 (Fig.3) previously set up obliquely, ~~and by~~. By passing the dipping former through the brush 10, the film 11 ~~affixed on~~coating the dipping former 3 is wound. ~~After~~Thus, after the leaching and subsequent drying treatments, the dipping former 3 is passed through the winding machine ~~8,8~~ and the film deposited ~~on~~on the dipping former is wound, before being removed from the former.

The A wound fingerstall ~~was made by the above instrument~~ is dried at 70 °C for 120 minutes to ~~make~~finish the product. This stall was easy to ~~wear~~don on the finger. ~~Regarding to the test for film strength, the~~The wound film was immediately unwound, dried at 70 °C for 60 minutes and subjected to the film strength test.

(Example 13)

In the same ~~way~~manner as described in Example 12, the dipping former was passed through the winding machine, and the wound fingerstall was unwound by the unwinding machine 9. The unwinding machine 9, as shown in Fig.4, rotates a roll type brush 10, and when the dipping former 3 is passed there, the machine unwinds the film 11 wound by the winding machine 8. The unwound fingerstall was dried in the drying furnace 7 at 90 °C for 5 minutes. After drying, the stall was again treated on the winding machine 8 and removed from the former to obtain the ~~product~~wound fingerstall.

This method of manufacturing the stall is evaluated to be highly practical, because ~~the drying of the product~~ is easy and the stall is easy to ~~wear~~put on and take off the finger because the winding operation is conducted twice. ~~For the film strength test, the~~The films were dried at 90 °C for 5 minutes prior to film strength testing.

(Example 14)

In the same ~~way~~manner as described in ~~Example~~Examples 12 and ~~13~~there13, wound fingerstalls were prepared ~~fingerstalls wound~~ by the winding machine 8, but the ~~manufactur~~manufacturing conditions were changed as follows. Namely, the dipping former was dipped in the latex liquid 1 cm more deeply than the portion deposited with the coagulant. Further, it was dipped in the external crosslinking agent 2 mm more shallowly than the portion where the coagulant is deposited. When these stalls are unwound, the ~~non~~-adhesive portions remain as a ~~wound mouth~~rolled lip. The unwound fingerstalls ~~became~~are straight fingerstalls with ~~wound mouth~~a rolled lip and the fingerstalls before unwinding ~~became~~are wound fingerstalls with ~~wound mouth~~rolled lip.

(Example 15)

(Wear Durability Test)

The A fingerstall of a non-adhesive carboxylated latex vulcanized with zinc oxide ~~gave~~showed very good strength in the strength test. But it was found that, when it was worn ~~actually~~, the portion of the fingerstall film of the portion whichthat was in contact with finger joints and finger bottoms broke in some cases ~~in~~within several hours. It is ~~considered~~may be that expansion and contraction ~~occur~~, which occurs during normal wear ~~because of~~, may cause the ionic ~~crosslinking~~ and that the crosslink points to gradually break down. This phenomenon ~~is hard to~~would most likely not occur in the case of sulfur vulcanization ~~which gives~~because they produce covalent ~~bonds~~bonds.

So, a little Ten slender, ~~ten~~ fingerstalls (16.5 mm in diameter) were worn ~~actually~~ on the middle finger ~~and~~or the ~~medical~~ring finger to investigate the number of stalls which will break after 24 hours. The results are shown in Table 2. When the emulsion latex is directly added with zinc oxide and ~~then~~an internally added aluminum type inorganic crosslinking agent such as aluminate and aluminum hydroxide gel (0.10 to 0.30 part as Al_2O_3), and ~~when the latex film undergoes~~ vulcanization ~~is conducted~~, surprisingly the fingerstalls did not break. Presumably, when the crosslink points of zinc break, the aluminum ion makes a ions crosslink and repairsreplace the broken crosslink points. The results are shown in Table 2 (also, refer to Table 12.)

The latex film forming conditions were the same as described in the paragraph mentioned below. ~~As a carboxyl group blocking agent for surface treatment,~~ polyaluminumhydroxidePolyaluminumhydroxide (Paho#2S, an aqueous solution of

0.025% as Al_2O_3) was used, and the as a carboxyl group blocking agent. The vulcanization temperature was 90 °C.

The compounds used in the examples are as follows:

Aluminumhydroxide gel

Aluminum hydroxide gel [Tomita]

(made by Tomita Seiyaku Co.)

Sodium aluminate

Sodium aluminate #2019

~~(made by Asada Kagaku Co.)~~

~~Polyaluminum hydroxide Pahe#2S~~

(made by Asada Kagaku Co.)

Polvaluminum hydroxide

Paho#2S

(made by Asada Kagaku Co.)

Table 2

Example No. 15	Content of added é éññ ññ Üäs é éññ ññpartÜj	0	0.10	0.15	0.20	0.25	0.30
	Number of broken stalls after 24 hour-wearing	10	5	2	0	0	0
	Content of added aluminumhydroxide gel Üäs é éññ ññpartÜj	0	0.10	0.15	0.20	0.25	0.30
	Number of broken stalls after 24 hour-wearing			2		0	

(Screening of Carboxyl Group Blocking Agent)

The following This screening was conducted for carboxyl-group blocking agents for ~~surface treatment~~ other than the external crosslinking agents of metal compounds having three or more valences. These compounds generally have low reactivity with carboxyl ~~group~~groups at low temperatures. Because of this, these compounds tend to diffuse in the Z-axis direction of the latex film ~~in~~during the steps of dipping and leaching ~~treatments~~. To reduce the ~~influence~~defect of the diffusion of the carboxyl-group blocking agent and to ~~restrain~~hinder the ~~reduction of the~~decrease in film strength, the latex was diluted to half the ~~neat~~original concentration and the concentration of calcium nitrate, an external coagulant, was increased to 300g/1000g from 150g/1000g.

Further, as mentioned below, ~~regarding with respect to~~ the reaction temperature of the latex film before ~~the its~~ strength is ~~expressed, since tested, because~~ a higher temperature is desirable for ~~the good~~ strength, the temperature ~~of at~~ the leaching step was changed to 75 °C. Further, to study the effect of the temperature ~~in at~~ the vulcanization step, the vulcanization temperature was set at two levels ~~of~~ 90 and 120 °C. The latex film forming conditions and the adhesion test conditions are as follows, unless otherwise ~~mentioned specified~~.

(Latex Film Forming Conditions)

Raw material latex: carboxylated NBR Nipol LX-551

Vulcanizing agent: active zinc ~~flower~~oxide 1.5 parts

Sodium aluminate or aluminum hydroxide 0.25
part (as Al₂O₃)

Solids concentration: adjusted to 22.5% by diluting with
water(dilution, 1:2)

Coagulant: calcium nitrate tetrahydrate; 300g/1000g

Carboxyl group blocking agent: 0.025% or 0.0025%

The dipping former is dipped in the coagulant solution.

The amount deposited onto the former is adjusted to
0.03g.

Dipping: The dipping former attached with the coagulant is dipped
in the latex solution. The dipping former is pulled up
after 5 seconds

Primary drying: 50 °C, 2 minutes

Leaching: 75 °C, 3 minutes

Drying: 90 °C, 1 minute

Outside surface treatment with carboxyl group blocking agent:

The latex film is dipped in the outside surface treatment
solution of 0.025% or 0.0025% carboxyl group blocking

agent. The amount attached ~~of to~~ the surface treatment ~~————— solution~~

was 0.03g.

Vulcanization: The latex film was vulcanized at 90 or 120 °C

for 5 minutes. The thickness of the latex film after vulcanization was 0.07 to 0.08 mm, and the weight was 0.3g.

(Adhesion Test-2)

The latex film prepared under the above-mentioned conditions is vulcanized, wound on the dipping former, and removed from the former as it is. The sample is heated in a hot air dryer ~~offor~~ for 90 °C for 30 minutes. Then, the sample is taken out from the dryer, cooled and unwound. The mark ○ indicates that unwinding is easy, the mark ~~△~~ indicates that unwinding becomes difficult on the way, the mark ~~indicates~~ × indicates that unwinding is considerably difficult and the mark ○' indicates that unwinding is slightly problematic.

(~~Example~~ Examples 16 to 18)

To confirm the effect of the addition of the aluminum type inorganic crosslinking agent that is internally added in the emulsion latex (aluminum hydroxide gel in ~~Example~~ Examples 16 to 18, sodium aluminate in ~~Example~~ Examples 35 and 61), ~~regarding~~ and the aluminum type external crosslinking agent for surface treatment (aluminum nitrate and polyaluminumhydroxide in Example 16, oxazoline compound in Example 17, and carbodiimide compound in Example 18), ~~there was studied~~ studies of the effect of the concentration of the carboxyl group blocking agent were conducted. Here, the vulcanization temperature of the aluminum type external crosslinking agent (aluminum nitrate or polyaluminum hydroxide) was 90 °C, and that of oxazoline and carbodiimide compounds was 120 °C.

In the case of the aluminum type external crosslinking agent, even when the emulsion latex ~~is~~ does not ~~added with~~ contain the internally added aluminum type inorganic crosslinking agent, the latex product becomes non-adhesive. When the internally added aluminum type inorganic crosslinking agent is used, the concentration of the carboxyl group blocking agent ~~for~~ needed to treat the surface ~~treatment~~ is lowered less.

On the other hand, in the case where the carboxyl group blocking agent ~~for to~~ treat the surface ~~treatment~~ is a water-soluble oxazoline compound or water-soluble carbodiimide compound, if the internally added aluminum type inorganic crosslinking

agent is not added, the effect of the carboxyl-group blocking agent ~~for surface treatment on non-adhesiveness~~ is small. However, although classified as compounds of the same kind, ~~in when the case of~~ carboxyl group blocking agent is an emulsion type carboxyl group blocking agent ~~for surface treatment~~, even when the internally added aluminum type inorganic crosslinking agent is not added, the ~~non-adhesion~~ adhesive effect on the surface is obtained. In the case of a water-soluble carboxyl group blocking agent ~~for to treat the surface treatment~~, the carboxyl-group blocking agent diffuses in the Z-axis direction to result in ~~a~~ the small effect ~~of by~~ the carboxyl-group blocking agent. On the other hand, if the internally added aluminum type inorganic crosslinking agent is added, the diffusion of the carboxyl-group blocking agent is ~~restrained~~ hindered, and, thus, ~~a non-adhesion~~ adhesive effect appears. The results are shown in Table 3. The compounds used in this example are as follows.

Aluminum hydroxide gel: aluminum hydroxide gel[Tomita]

(made by Tomita Seiyaku Co.)

Polyaluminum hydroxide: Paho#2S (made by Asada Kagaku Kogyo Co.)

Oxazoline compound: Epocross W (aqueous solution)

(made by Nihon Shokubai Co.)

Epocross K-2030(emulsion)

(made by Nihon Shokubai Co.)

Carbodiimide compound: Carbodilite E-01(emulsion)

(made by Nisshinbo Co.)

Carbodilite V-02(aqueous solution)

(made by Nisshinbo Co.)

Example 35 used a modified polyamine polyurea resin(Sumirez Resin 712). This resin is so reactive that it causes the latex to coagulate when added to the latex. ~~In the case of such a compound, as in~~ With these compounds, much like the aluminum type external crosslinking agent, ~~non-adhesion effect appears in even a system to which the~~ adhesive effects appear even if an internally added aluminum type inorganic crosslinking agent is not added. Further, alkylketene dimer of Example 61 ~~is~~ 61, an emulsion ~~and, is reactive, and, as with~~ the emulsion emulsions of ~~Example~~ Examples 17 and 18, ~~so even the system in which the~~ if an internally added aluminum type

inorganic crosslinking agent is not added—~~possesses the~~, they have a non-
~~adhesion~~adhesive effect.

Table 3 Content of internally added aluminum type inorganic crosslinking agent (as Al₂O₃) (part)

					Concentration of Chemical						
Example No.	Carboxyl-group blocking agent for surface treatment	Trademark		Vulcanization temp.	1.0%	0.25%	0.025%	0.0025%	0.001%		
16	Aluminum compound	Al(NO ₃) ₃ (aq. solution)	Aluminum hydroxide gel	0	90°C	○	○	○'	×		
				0.25	90°C		○	○	△		
		Paho#2S (polyaluminum hydroxide) (aq. solution)		0	90°C		○	○	×		
				0.25	90°C		○	○	△		
17	Oxazoline compound	Epocross K2030 (emulsion)		0	120°C	○	△				
				0.25	120°C		○	○	○		
		Epocross W (aq. solution)		0	120°C	×	×				
				0.25	120°C		○	○	○	○	
18	Carbodiimide compound	Carbodilite E-01 (emulsion)		0	120°C	○	○	△			
				0.25	120°C		○	○'	△		
		Carbodilite V-02 (aq. solution)		0	120°C	△	×				
				0.25	120°C		○	○	△		
35	Modified Polyamine polyurea resin	Sumirez Resin 712 (aq. solution)	Sodium aluminate	0	90°C	○	○	○	×		
				0	120°C	○	○	○	×		
				0.25	90°C	○		○	○'		
				0.25	120°C	○		○	○'		
61	Alkylketene dimer	Hasize AK-720H (emulsion)		0	90°C	○	○	○			
				0	120°C	○	○	○			
				0.25	90°C			○	○		
				0.25	120°C			○	○		

(Example 19)

~~Next, to To~~ study the influence of the diffusion of the carboxyl group blocking agent for ~~treating a surface treatment, there was studied,~~ the effect of a-temperature ~~of at~~ the leaching step before vulcanization was studied.

~~As the carboxyl group blocking agent, the~~ The water-soluble oxazoline compound (Epocross W, made by Nippon shokubai Co.) was used as the carboxyl-group blocking agent. The concentration was varied from 0.1% to 0.001%, and the temperature ~~of at~~ the leaching step was varied from 50 to 75 °C. The results are shown in Table 4.

~~In the case of the treatment concentration~~ For concentrations as high as 0.1%, when the leaching step temperature is low, the film strength becomes low and the non-adhesion ~~adhesive~~ effect tends to be low.

~~It is considered that, even in the case that the~~ Even when an internally added aluminum type inorganic crosslinking agent (sodium aluminate, 0.25 part as-Al₂O₃) was added, ~~there appeared the influence of the diffusion in at~~ low temperatures could be noted.

Table 4

Example No.	Carboxyl-group crosslinking organic agent for surface treatment	Conc.		Temp. of leaching step					
				50°C	55°C	60°C	65°C	70°C	75°C
19	Oxazoline compound Epocross W	0.1%	Adhesion test	×	○	○	○		○
			Strength (Mpa)		27.9	31.8	29.8	30.5	37.7
		0.025%	Adhesion test	×	○	○	○	○	○
			Strength (Mpa)						37.3
		0.005%	Adhesion test						
			Strength (Mpa)						35.1
		0.001%	Adhesion test	×					○
			Strength (Mpa)						35.1

(Example 20 to 27)

~~Regarding to~~ Studies of how the concentration of the compounds considered as ~~crosslinking to be cross linking agents for the~~ carboxyl group, ~~there was studied how the concentration of the i.e. carboxyl group blocking agent agents for treating the surface treatment,~~ and the vulcanization temperature (90 and 120 °C) ~~had effect on °C~~ affect the non-adhesion ~~in the system in which the of latex film where an~~ internally added

aluminum type inorganic crosslinking agent ~~was~~is added to the latex were conducted.
The test results are shown in Table 5.

Carboxyl group blocking agents for treating a surface ~~treatment~~-(i.e., organic crosslinking agents for carboxyl ~~group~~groups):

(Example 20) polyamine triethylenetetramine(made by Wako Seiyaku)

(Example 21) melamine resin, Sumitex Resin M-3 (made by Sumitomo Kagaku Kogyo)

(Example 22) melamine resin, Sumirez Resin 613special (made by Sumitomo Kagaku Kogyo)

(Example 23) amino group-containing urethane resin, Superflex R-3000 (made by Daiichi Kagaku Kogyo)

(Example 24) blocked isocyanate prominate, XC-915 (made by Takeda Yakuhin Kogyo)

(Example 25) multifunctional epoxy compound, Denacol EX-614B (made by Nagase Kasei Kogyo)

(Example 26) epoxycresolnovolac resin emulsion, Denacol EM-150 (made by Nagase Kasei Kogyo)

(Example 27) bifunctional epoxy compound, Denacol EX-313 (made by Nagase Kasei Kogyo)

Table 5

Example No.	Carboxyl-group crosslinking organic agent for surface treatment	Trademark	Vulcanization temp.	Conc. of organic crosslinking agent			
				0.025%	0.01%	0.005%	0.0025 %
20	Polyamine	Triethyltetramine	90°C	○			
			120°C	△			
21	Melamine resin	Sumitex Resin M-3	90°C	○			
			120°C	△			
22	Melamine resin	Sumitex Resin 613special	90°C	○		○	
			120°C	○			
23	Amino group-containing urethane resin	Superflex R-3000 (urethane)	90°C	○		○	
			120°C	○			
24	Blocked isocyanate	Prominate XC-915	90°C	○			
			120°C	○			
25	Polyfunctional epoxy compound	Denacol EX-614B	90°C	△	○	○	
			120°C	○	○		
26	Epoxycresolnovolac resin	Denacol EM-150	90°C	○			○
			120°C	○			○
27	Bifunctional epoxy compound	Denacol EX-313	90°C	○		○	
			120°C	○			

(~~Example~~Examples 28 to 36)

In the same manner as in ~~Example~~Examples 20 to 27, ~~regarding the~~hydrogen bond formation regulators used in the field of paper, ~~the test was conducted~~were tested to evaluate their performance as carboxyl group blocking agent. These compounds have been developed as waterproof endowing agent, printability improver, wet paper strength reinforcing agent and the like ~~of papers~~for paper, with their workability and safety taken into consideration. The results are shown in Table 6. As in the case of ~~the~~ organic crosslinking ~~agent~~agents for carboxyl ~~group~~groups, the compounds ~~give~~the~~have a non-adhesion~~adhesive effect.

~~As to~~In Example 35, ~~the~~a test was conducted ~~for the system in which the~~where an internally added aluminum type inorganic crosslinking agent, sodium aluminate, was not added.

Carboxyl group blocking agent for treating a ~~surface treatment~~ (i.e., hydrogen bond formation regulators):

(Example 28) glyoxal (made by Wako Junyaku Co.)

(Example 29) polyamide resin, Sumirez Resin 5001 (made by Sumitomo Kagaku Kogyo Co.)

(Example 30) polyamide resin, Sunmide X-13A (made by Sanwa Kagaku Kogyo Co.)

(Example 31) polyamidepolyurea resin, Sumirez Resin 636 (made by Sumitomo Kagaku Kogyo Co.)

(Example 32) polyamideepoxy resin, Sumirez Resin 675 (made by Sumitomo Kagaku Kogyo Co.)

(Example 33) polyaminepolyurea resin, Sumirez Resin 302 (made by Sumitomo Kagaku Kogyo Co.)

(Example 34) polyaminepolyurea resin, PA-620 (made by Nippon PMC)

(Example 35) modified polyaminepolyurea resin, Sumirez Resin 712 (made by Sumitomo Kagaku Kogyo Co.)

(Example 36) polyamidepolyureaglyoxal condensation reaction product, Sumirez Resin 5004 (made by Sumitomo Kagaku Kogyo Co.)

Table 6

Example No.	Hydrogen bond formation regulator for surface treatment	Trademark	Vulcanization temp.	Conc. of reactive organic compound			
				0.025%	0.01%	0.005%	0.0025%
28	Glyoxal		90°C	△			
			120°C	○			
29	Polyamide resin	Sumirez Resin 5001	90°C	○		○	○
			120°C	○			○
30	Polyamide resin	Sunmide X-13A	90°C	○			
			120°C	○			
31	Polyamide polyurea resin	Sumirez Resin 636	90°C	○			○
			120°C	○			○
32	Polyamide epoxy resin	Sumirez Resin 675	90°C	○'			
			120°C	○			
33	Polyamine polyurea resin	Sumirez Resin 302	90°C	○			○'
			120°C	○			○
34	Polyamine polyurea resin	PA-620	90°C	○			
			120°C	○			
35	Modified polyamine polyurea resin	Sumirez Resin 712	90°C	○		○	○'
			120°C	○			○'
		NaAlO ₂ not added	90°C	○			×
			120°C	○			×
36	Polyamidepolyureaglyoxal condensation reaction product	Sumirez Resin 5004	90°C	○	○'	○	
			120°C	○			

~~(Example~~(Examples 37 to 39)

The test was Tests were conducted in the same manner as in ~~Example~~Examples 20 to 34 concerning ~~the~~a monofunctional carboxyl group blocking agent. The results are shown in Table 7. The agent, which is monofunctional, cannot crosslink a carboxyl group, and yet it has ~~the~~a non-adhesionadhesive effect. It is ~~noticed~~noted that blocking a carboxyl group and forming hydrophobicity are both important for the non-adhesion of the latex product.

Surface carboxyl blocking agents for treating a surface~~treatment~~ (i.e., monofunctional carboxyl blocking agents):

(Example 37) monofunctional modified bisphenol A type epoxy emulsion, Denacast EM-101 (made by Nagase Kasei Kogyo Co.)

(Example 38) monofunctional modified bisphenol A type epoxy emulsion, Denacast EM-103 (made by Nagase Kase Kogyo Co.)

(Example 39) monofunctional epoxy, Denacol EX-145 (made by Nagase Kasei Kogyo Co.)

Table 7

Example No.	Monofunctional carboxyl-group blocking agent for surface treatment	Trademark	Vulcanization temp.	Conc. of monofunctional carboxyl-group blocking agent			
				0.025%	0.01%	0.005%	0.0025%
37	Monofunctional epoxy	Denacast EM-101 (emulsion)	90°C	○			
			120°C	○			
38	Monofunctional epoxy	Denacast EM-103 (emulsion)	90°C	○		○	○'
			120°C	○			○
39	Monofunctional epoxy	Denacol EX-145	90°C	○			
			120°C	○			

(Example 40 to 58)

In the same manner as in ~~Example~~Examples 20 to 39, the non-adhesion surfactants (cationic, amphoteric, nonionic, or anionic) were tested for their performance as carboxyl-group blocking agents, including a test for the effect of adding an internally added aluminum type inorganic crosslinking agent, sodium aluminate. The results are shown in Table 8. ~~In the system in which~~Where sodium aluminate was not added, the non-adhesion~~adhesive~~ effect of the surfactant is small.

Carboxyl group blocking agent for treating a surface treatment (non-adhesive surfactant):

Non-adhesion~~adhesive~~ cationic surfactant:

(Example 40) quarternary amine, Quartermin 86W (made by Kao Co.)

(Example 41) quarternary amine, Catinal MB 50A (made by Toho Kagaku Kogyo)

(Example 42) imidazoline type betaine, Anhitol 20YB (made by Kao)

(Example 43) oxide type betaine, Softamin L (made by Toho Kagaku Kogyo)

(Example 44) alkylamide type betaine, Ovazolin CAB-30 (made by Toho Kagaku Kogyo)

Non-adhesive nonionic surfactant:

(Example 45) tertiary amine, Esomin C/12 (made by Lion)

(Example 46) tertiary alkylamine, Amito 105 (made by Kao)

(Example 47) alkanolamide, Aminon PK-02S (made by Kao)

(Example 48) polyoxyethylenelauryether, Emulgen 109P (made by Kao)

(Example 49) polyoxyethylene derivative, Emulgen A60 (made by Kao)

Non-adhesive anionic surfactant:

(Example 50) β -naphthalenesulfonic acid formalin condensation product, Demol N (made by Kao)

(Example 51) alkylmethyltaurinate, Lipotac TE (made by Lion)

(Example 52) disodium dodecylphenylethersulfonic acid, Perex SS-L (made by Kao)

Table 8

Example No.		Non-adhesive surfactant for surface treatment	Trademark	Vulcanization temp.	Conc. of surfactant			
					0.025%	0.01%	0.005%	0.0025%
40	Cation	Quaternary amine	Quartermin 86W	90°C	○			
				120°C	○			
				NaAlO ₂ not added	90°C	×		
				120°C	×			
41	Cation	Quaternary amine	Catinal MB-50A	90°C	○'			○'
				120°C	○			○
				NaAlO ₂ not added	90°C	×		×
				120°C	×			×
42	Amphoteric	Imidazoline type betaine	Anhitol 20YB	90°C	○	○'	△	
				120°C	○			
				NaAlO ₂ not added	90°C	×	×	×
				120°C	×			△
43	Amphoteric	Oxide type betaine	Softamin L	90°C	△			○
				120°C	○			○
				NaAlO ₂ not added	90°C	×		×
				120°C	×			×
44	Amphoteric	Alkylamide type betaine	Ovazolin CAB-30	90°C	○		○	
				120°C	○			
				NaAlO ₂ not added	90°C	×	×	
				120°C	×			
45	Nonion	Tertiary alkylamine	Esomin C/12	90°C	○'			○'
				120°C	○			○
				NaAlO ₂ not added	90°C	×		×
				120°C	×			×
46	Nonion	Tertiary alkylamine	Amito 105	90°C	△			
				120°C	○			
				NaAlO ₂ not added	90°C	×		
				120°C	×			

47	Nonion	Alkanolamide (lauryldiethanolamide)	Aminon PK-02S	90°C	○	○	△	
				120°C	○			
				NaAlO ₂ not added	90°C	×	×	×
				120°C	×			
48	Nonion	Polyoxyethylene laurylether	Emulgen 109P	90°C	△			
				120°C	○			
				NaAlO ₂ not added	90°C	×		
				120°C	×			
49	Nonion	Polyoxyethylene derivative	Emulgen A60	90°C	△			
				120°C	○			
				NaAlO ₂ not added	90°C	×		
				120°C	×			
50	Anion	β-naphthalenesulfonic acid formalin condensation product	Demol N	90°C	○			○'
				120°C	○			○
				NaAlO ₂ not added	90°C	×		×
				120°C	×			×
51	Anion	Alkylmethyltaurinate	Lipotac TE	90°C	○'			△
				120°C	○			
				NaAlO ₂ not added	90°C	×		×
				120°C	×			×
52	Anion	Disodium dodecyldiphenylethersul fonate	Perex SS-L	90°C	△			
				120°C	○'			
				NaAlO ₂ not added	90°C	×		
				120°C	×			

(~~Example~~Examples 53 to 58)

Regarding To evaluate the performance of polymer type derivatives, ~~to evaluate their performance as carboxyl group blocking agent, the test was agents, tests were~~ conducted in the same manner as in ~~Example~~Examples 40 to 52. Although these compounds are sometimes treated as polymer surfactant, they ~~are employed~~were used as non-adhesive polymer type surfactants in the present invention. The results are shown in Table 9.

Carboxyl group blocking agent for treating a surface~~treatment~~ (i.e., non-adhesive polymer type surfactants):

(Example 53) cellulose derivative, Reoguard KGP (made by Lion)

(Example 54) cationized starch, CATO 308 (made by Nippon NSC)

(Example 55) cationized starch, Opti Bond 3282 (made by Nippon NSC)

(Example 56) dimethyldiallyammoniumchloride acrylamide copolymer, ME polymer 09W (made by Toho Kagaku Kogyo)

(Example 57) cationic polyurethane dispersion in water, F-8570D (made by Daiichi Kogyo Seiyaku)

(Example 58) ammonium polystyrenesulfonate, VERSA-TLYE915 (made by Nippon NSC)

Table 9

Example No.		Non-adhesive polymer surfactant for surface treatment	Trademark	Vulcanization temp.	Conc. of polymer surfactant			
					0.025%	0.01%	0.005%	0.0025%
53	Cation	Cellulose derivative	Reoguard KGP	90°C	△			
				120°C	○			
				NaAlO ₂ not added	90°C	×		
				120°C	×			
54	Cation	Cationized starch	CATO 308	90°C	○			△
				120°C	○			○'
				NaAlO ₂ not added	90°C	×		
				120°C	×			
55	Cation	Cationized starch	Opti Bond 3282	90°C	○'			
				120°C	○			
				NaAlO ₂ not added	90°C	×		
				120°C	×			
56	Cation	Dimethyldiallylammonium chloride acrylamide copolymer	ME polymer 09W	90°C	○'			
				120°C	○			
				NaAlO ₂ not added	90°C	×		
				120°C	×			
57	Cation	Cationic polyurethane dispersion in water	F-8570D	90°C	○			
				120°C				
				NaAlO ₂ not added	90°C	×		
				120°C				
58	Anion	Ammonium polystrenesulfonate	VERSA-TLYE915	90°C	△			
				120°C	○			
				NaAlO ₂ not added	90°C	×		
				120°C	×			

~~(Example~~(Examples 59 to 64)

~~Regarding paper sizing agents, to~~ To evaluate theirthe performance of paper sizing agents as carboxyl group blocking agent, the test wasagents, tests were conducted in the same waymanner as in ExampleExamples 20 to 39. The results are shown in Table 10. ConcerningIn Example 61, the test was conducted for the system in which thean internally added aluminum type inorganic crosslinking agent, sodium aluminate, was not added.

Carboxyl group blocking agent for treating a surface treatment—(i.e., sizing agent):

(Example 59) fortified rosin, Sizepine E-50 (made by Arakawa Kagaku Kogyo). This sizing agent coagulates with a calcium salt. So, the treatment of the inside surface was

conducted with Sizepine N-773 (concentration: 0.0025%) mentioned below, and the treatment of the outside surface was conducted with Sizepine E.

(Example 60) emulsion type rosin sizing agent, Sizepine N-773 (made by Arakawa Kagaku Kogyo)

(Example 61) alkylketene dimer, Hasize AK-720H (made by Harima Kasei)

(Example 62) styrene type synthetic sizing agent, BLS-720 (made by Misawa Ceramics)

(Example 63) olefin type synthetic sizing agent, Hamacoat AK-505 (made by Misawa Ceramics)

(Example 64) alkenyl succinate, Sizepine (made by Arakawa Kagaku Kogyo)

Table 10

Example No.	Sizing agent for surface treatment	Trademark	Vulcanization temp.	Conc. of sizing agent	
				0.025%	0.0025%
59	Fortified rosin sizing agent	Sizepine E-50	90°C	○	
			120°C	○	
60	Emulsion type rosin sizing agent	Sizepine N-773	90°C	○	○
			120°C	○	○
61	Alkylketene dimer	Hasize AK-720H	90°C	○	○
			120°C	○	○
		NaAlO ₂ not added	90°C	○	
			120°C	○	
62	Styrene type synthetic sizing agent	BLS-720	90°C	○	○
			120°C	○	○
63	Olefin type synthetic sizing agent	Hamacoat AK-505	90°C	○	○
			120°C	○	○
64	Alkenyl succinate	Sizepine S-400S	90°C	○	○
			120°C	○	○

~~(Example~~(Examples 65 to 81)

The performance test was Performance tests were conducted for carboxyl group blocking agents in the same manner as in ~~Example~~Examples 20 to 64. The carboxyl-group blocking agents were directly added to the latex to confirm their effect. Accordingly, the latex film was immediately vulcanized after the leaching treatment to make each sample. ~~The~~An adhesion test was conducted according to ~~the~~ adhesion test

2. The results are shown in Table 11. It is ~~noticed~~noted that any type of carboxyl group blocking ~~agents~~agent for treating a surface treatment is effective as an internally added carboxyl-group blocking agent. However, ~~such a~~ carboxyl-group blocking agent that coagulates the latex when it is incorporated into a latex emulsion is not desirable. In ~~such a case~~these cases, it is necessary to take ~~a measure~~additional measures such as stabilizing the latex emulsion by adding a surfactant. Also studied was the ~~influence~~effect of ~~addition of an~~adding the internally added aluminum type inorganic crosslinking agent, sodium aluminate. In the case of a reactive carboxyl-group blocking agent (in ~~Example~~Examples 70 and 77) and a carboxyl-group blocking agent which forms an insoluble salt with calcium ion (in ~~Example~~Examples 76, 78 and 81), the non-adhesion~~adhesive~~ effect ~~appears~~occurs even ~~in the system in which~~when sodium aluminate is not added. When a polyamide polyurea resin (Sumirez Resin 703) is added, the latex emulsion is ~~coagulated without addition of~~coagulates if sodium aluminate, ~~but with addition of it, the sodium aluminate is not added. However, when sodium aluminate is added, it disperses the Sumirez Resin 703 homogeneously. Thus, without a non-adhesive effect is observed and coagulation of the emulsified latex, the non-adhesion effect is observed is prevented.~~

Internally added carboxyl group blocking agents:

(Example 65) monofunctional modified bisphenol A type epoxy emulsion, Denacast EM-103 (made by Nagase Kasei Kogyo)

(Example 66) carbodiimide crosslinking agent, Carbodilite V-20 (made by Toyobo)

(Example 67) oxazoline crosslinking agent, Epocross W (made by Nihon Shokubai)

(Example 68) self-emulsifying type polyisocyanate, Aquanate 200 (made by Nihon Polyurethane Kogyo)

(Example 69) blocked isocyanate, Prominate XC-915 (made by Takeda Seiyaku)

(Example 70) polyamide resin, Sumirez Resin 5001 (made by Sumitomo Kagaku Kogyo)

(Example 71) polyamidepolyurea resin, Sumirez Resin 703 (made by Sumitomo Kagaku Kogyo)

(Example 72) β -naphthalenesulfonic acid formalin condensation ~~product~~product, Demol N (made by Kao)

(Example 73) alkyl naphthalenesulfonic acid formalin condensation polymerization product, Polyty N-100 (made by Lion)

(Example 74) alkylmethyltaurate, Lipotac TE made by Lion)

(Example 75) emulsion type modified rosin sizing agent, Halfsize NES-650 (made by Harima Kasei)

(Example 76) fortified rosin sizing agent, Sizepine (made by Arakawa Kagaku Kogyo)

(Example 77) alkylketene dimer, Halfsize AK-720H (made by Harima Kasei)

(Example 78) alkenylsuccinate, Sizepine S-400S (made by Arakawa Kagaku Kogyo)

(Example 79) alkenylsuccinic acid anhydride, Coloppearl Z-100S (made by Seiko Kagaku Kogyo)

(Example 80) styrene acryl type surface sizing agent, Coloppearl M-150-2 (made by Seiko Kagaku Kogyo)

(Example 81) saponification product of an adduct of branched olefin and maleic anhydride, RFsize NSP-SH (made by Seiko Kagaku Kogyo)

Table 11

Example No.	Internally added carboxyl-group blocking agent	Trademark	Vulcanization temp.	Amount added (part)	
				2.5	1.0
65	Monofunctional epoxy	Denacast EM-103	90°C	○'	×
			120°C	○'	○
			NaAlO ₂ not added	90°C	×
			120°C	×	
66	Carbodiimide	Carbodilite V-02	90°C	○'	○'
			120°C	○'	○
			NaAlO ₂ not added	90°C	×
			120°C	×	
67	Oxazoline	Epocross W	90°C	○	○'
			120°C	○	○
			NaAlO ₂ not added	90°C	×
			120°C	×	
68	Self-emulsifying polyisocyanate	Aquanate 200	90°C		○'
			120°C		○
			NaAlO ₂ not added	90°C	×
			120°C	×	
69	Blocked isocyanate	Prominate XC-915	90°C		○
			120°C		○
			NaAlO ₂ not added	90°C	×
			120°C	△	
70	Polyamide resin	Sumirez Resin 5001	90°C	○	○
			120°C	○	○
			NaAlO ₂ not added	90°C	△
			120°C	○'	
71	Polyamide polyurea resin	Sumirez Resin 703	90°C	○	○'
			120°C	○	○
			NaAlO ₂ not added	90°C	aggregate
			120°C		
72	β-naphthalenesulfonic acid formalin condensate	Demol N	90°C	○	○'
			120°C	○	○
			NaAlO ₂ not added	90°C	×
			120°C	△	
73	Alkyl naphthalenesulfonic acid formalin condensate	Polyty N-100K	90°C		△
			120°C		○
			NaAlO ₂ not added	90°C	×
			120°C	×	
74	Alkylmethyltaurinate	Lipotac TE	90°C	○	×
			120°C	○	○
			NaAlO ₂ not added	90°C	×
			120°C	△	
75	Emulsion type rosin sizing agent (modified rosin)	Hasize NES-650	90°C	○'	△
			120°C	○	○
			NaAlO ₂ not added	90°C	×
			120°C	△	

76	Fortified rosin sizing agent	Sizepine E-50	90°C	○	×
			120°C	○	○
		NaAlO ₂ not added	90°C	△	
			120°C	○'	
77	Alkylketene dimer	Hasize AK-720H	90°C	○	○
			120°C	○	○
		NaAlO ₂ not added	90°C	×	
			120°C	○'	
78	Alkenyl succinate	Sizepine S-400S	90°C	○	○'
			120°C	○	○
		NaAlO ₂ not added	90°C	○'	
			120°C	○	
79	Alkenyl succinic acid anhydride	Coropearl Z-100S	90°C	○	○'
			120°C	○	○
		NaAlO ₂ not added	90°C	×	
			120°C	△	
80	Styrene-acryl type surface sizing agent	Coropearl M-150-2	90°C	○	△
			120°C	○	○
		NaAlO ₂ not added	90°C	×	
			120°C	△	
81	Branched olefin-maleic anhydride adduct	RF size NSP-SH	90°C		△
			120°C		○
		NaAlO ₂ not added	90°C	○'	
			120°C	○	

(~~Example~~Examples 82 to 85)

Fingerstalls were prepared in the same ~~way~~manner as in Example ~~29~~29, except that internally added aluminum type inorganic crosslinking agents, as described below, were used in place of sodium aluminate. Adhesion and ~~the adhesion and wear~~ durability tests were conducted. The amount of ~~the~~ internally added aluminum type inorganic crosslinking agent was 0.25 part-as Al₂O₃. The carboxyl-group blocking agent used was polyamide resin (Sumirez Resin 5001). The concentration of the polyamide resin for treating the surface treatment was 0.025%. The results are shown in Table 12. As in the case of Example 29, the latex film was non-adhesive. Any fingerstall that did not break in the ~~wear~~-durability test, ~~thus~~ passed the test.

(Example 82) calcium aluminate (made by Soekawa Rikagaku)

(Example 83) magnesium aluminate (made by Soekawa Rikagaku)

(Example 84) aluminum magnesium hydroxide, Aluminum magnesium hydroxide 251 (made by Tomita Seiyaku)

(Example 85) synthetic hydrotalcite, Synthetic hydrotalcite H (made by Tomita Seiyaku)

Table 12

Example No.	Internally added aluminum type inorganic crosslinking agent	Trademark	Vulcanization temp.	Adhesion test 2	Number of breakings
82	Calcium aluminate		90°C	△	0
			120°C	○	0
83	Magnesium aluminate		90°C	△	0
			120°C	○	0
84	Aluminum · magnesium hydroxide	Aluminum · magnesium hydroxide 251	90°C	○	0
			120°C	○	0
85	Synthetic hydrotalcite	Synthetic hydrotalcite	90°C	○'	0
			120°C	○	0

(Example 86)

In manufacturing fingerstalls in the same waymanner as in ~~Example~~Examples 2 and 3, the dipping former was dipped and deposited with ~~thean~~ external crosslinking agent for the inside surface, dried, and dipped in the methanolic external coagulant liquid 1 cm more deeply than the portion of ~~saidthe~~ crosslinking agent and dried. Then, the former was dipped in the latex slightly more shallowly than the part of the methanolic external coagulation liquid, ~~and further it.~~ The former was then dipped in the external crosslinking liquid for the outside surface ~~into~~ the same depth as the external crosslinking agent for the inside surface. When these stalls are wound and then unwound, the ~~non~~-adhesive portions remain as-wound ~~mouth~~as the rolled lip. In this case, since the latex is not directly brought into contact with the dipping former and since the thickness of the latex is increased due to the coagulation liquid, the removal of the latex film from the dipping former is easy and the winding is also easy.

(Example 87)

In forming fingerstalls in the same waymanner as in ~~Example~~Examples 14 and 86, the ~~wound mouth~~rolled lip was formed after the former was dipped in the latex. ~~By coating— but before exposure to an external crosslinking liquid. By then coating an external crosslinking liquid for the outer surface, non-adhesive fingerstalls with wound mouth coulda~~ rolled lip can be formed. In this case, even if the former is immersed in

the external crosslinking liquid more deeply than the ~~wound-mouth~~rolled lip portion, the ~~wound-mouth~~rolled lip does not unwind and so it is not necessary to mind the depth of the external crosslinking liquid on the outer surface.

(Example 88)

In forming fingerstalls in the same ~~way~~manner as in Example 4, the former was immersed in the latex more shallowly than the external coagulation liquid and the external crosslinking liquid to form a ~~wound-mouth~~rolled lip. As in Example 86, since the latex has an increased thickness owing to the coagulation liquid, the removal of the latex-formed film from the dipping former is easy and ~~making~~winding the ~~bottom~~windingsfingerstall is also easy. ~~In this case, if~~ the latex is too dry when a ~~wound~~mouthrolled lip is formed, the ~~wound-mouth~~unwindsrolled lip may unwind. But, if the ~~wound-mouth~~rolled lip is made when the latex is half gelled, and ~~if it is~~then dried, it does not unwind.

(Example 89)

Fingerstalls were formed using the ~~trial-use~~fingerstall manufacturing equipment (Fig.2) under the same latex film forming conditions as ~~used in the said~~used screening of carboxyl-group blocking agents. The former was immersed in the coagulation liquid and dried, and, thereafter, immersed in the latex incorporated with 1.5 parts of zinc oxide, 0.25 part (as Al_2O_3) of sodium aluminate and 1.5 parts of zinc oxide, and then dried. After being subjected to the ~~treatments of mouth-lip~~ winding, leaching and drying, the former was immersed in the ~~an~~outside surface treating agent of 0.025% polyamide resin, Sumirez resin 5001 (made by Sumitomo Kagaku Kogyo) and dried at 90 °C for 2 minutes. Thereafter, winding and unwinding of the fingerstall were successively conducted, ~~and, the~~. The film was dried at 90 °C for 3 minutes, again wound on the winding machine and removed from the former in the wound state. ~~In the ease of the~~With inorganic outside-surface treating ~~agent~~agents, ~~the~~a leaching treatment is necessary after immersion into the outside-surface treating agent. Since ~~this~~the present outside-surface treating agent is organic, the leaching treatment is unnecessary after the immersion into the outside-surface treating agent. Hence, the ~~manufacture~~manufacturing steps can be reduced.

The stalls removed from the former were dried at 70 °C for 120 minutes to give the final products. The formed stalls were easy to ~~wear~~don on ~~finger~~the fingers.

(Example 90)

Fingerstalls were formed in the same ~~way~~manner as in Example 86 except that the latex was incorporated with 1 part of alkylketene dimer, Halfsize AK-720H (made by Harima Kasei) as the carboxyl-group blocking agent. In this case, since the carboxyl-group blocking agent is added to the latex, it is not necessary to ~~deposited~~deposit the outside-surface treating agent after dipping the former into the latex. Hence, the ~~manufacture~~manufacturing steps can be reduced. The ~~manufacture~~manufacturing steps are as follows. The former ~~was~~is dipped in the coagulation liquid and dried, then dipped in the latex and dried, subjected to a leaching treatment after winding the mouth, and dried at 90 °C at 2 minutes. Thereafter, winding and unwinding were successively conducted, and the film was dried at 90 °C for 3 minutes. It was again wound on the winding machine and removed from the former in the wound state.

~~The fingerstalls~~ Fingerstalls removed from the former ~~was~~were dried at 70 °C for 120 minutes to give the final ~~product~~products. The stalls were easy to ~~wear~~don on ~~finger~~the fingers.

~~Next, shown~~ The following are examples of non-adhesive carboxylated latex products which have a layer treated with a carboxyl group blocking agent on the inside surface of the carboxylated latex products and ~~which have a chlorination treatment on the~~whose outside surface ~~thereof~~has been chlorinated.

1. Preparation of a raw material latex

A raw material latex (carboxylated NBR Nipol LX-551, made by Nippon Zeon) was added with 1.5 parts of activated zinc ~~flow~~eroxide and 0.25 part (as Al₂O₃) of aluminum hydroxide gel as the vulcanizing agent. The mixture was diluted with water or water and a carboxyl group blocking agent to adjust the ~~solids~~-concentration of solids to 22.5%.

2. Preparation of a coagulant solution

A coagulant aqueous solution of calcium nitrate tetrahydrate 300g/1000g was prepared. When the inside surface of the product was treated with a carboxyl group

blocking agent, the carboxyl group blocking agent was added into the coagulant aqueous solution.

3. Formation of a film of carboxylated synthetic rubber latex

A former, which had been dipped in the coagulant liquid and ~~attached~~coated with the coagulant, was dipped into a liquid of the above-mentioned carboxylated synthetic rubber latex. After 5 seconds' ~~residence~~, a latex film was formed. The thickness of the latex film was 0.08 mm. The film was predried at 50 °C for 2 minutes and subjected to a leaching treatment at 75 °C for 3 minutes. Then, the film was dried at 90 °C for 1 minute, dipped into a chlorine aqueous solution having a chlorine concentration of 0.4 g for 5 seconds, and thereafter heated at 90 °C for 5 minutes. The latex film, thus prepared, was wound on the former and removed from the former. This sample was subjected to an adhesion test. The adhesion test was conducted by heating the sample, a wound film, at 90 °C for 30 minutes and ~~by~~ unwinding after cooling. ~~The ease~~Cases where the unwinding was easy ~~was~~is denoted by ○, ~~the case where the unwinding became not easy on the way by —, the case;~~ cases where the wound film could not be easily unwound to the end from the middle of the fingerstall is denoted by △; and cases where the unwinding was considerably difficult is denoted by ×.

(Comparative example 8)

~~With~~Under the above-mentioned conditions but without addition of the carboxyl group blocking agent either in the coagulant or in the latex, a latex film was prepared subjected only withto a chlorination treatment on the outside surface ~~and subjected to~~. This latex film was put through the adhesion test. The results are shown in Table 13. The sample, after the adhesion test, was considerably difficult to unwind.

Table 13

Comparative Example No.	Internally added carboxyl-group blocking agent and Carboxyl-group blocking agent for surface treatment	Adhesion Test
8	none	×

(Example 91)

The results of ~~the~~an adhesion test of a sample, obtained by ~~internally~~-adding in the latex a sizing agent as the carboxyl group blocking agent and chlorinating the outside surface, are shown in Table 14. The carboxyl group blocking agent used in the example is as follows.

(Example 91) Fortified rosin sizing agent Sizepine E-50 (made by Arakawa Kagaku Kogyo)

Table 14

Example No.	Internally added carboxyl-group blocking agent	Trademark	Amount added (part)	Adhesion Test
91	Fortified rosin sizing	Sizepine E-50	2.5	○

(Examples 92-94)

The results of ~~the~~-adhesion testtests of samples, obtained by ~~internally~~-adding in the latex organic crosslinking agents as the carboxyl group blocking agent and chlorinating the outside ~~surfaces~~surface, are shown in Table 15. The carboxyl group blocking agents used in the examples are ~~each as in the followings~~follows.

Table 15

Example No.	Internally added carboxyl-group blocking agent	Trademark	Amount added (part)	Adhesion Test
92	Blocked isocyanate	Prominate XC-915	1	○
93	Oxazoline	Epocross WS-500	2.5	○
94	Monofunctional epoxy	Denacast EM-103	2.5	○

(Example 92) Blocked isocyanate Prominate XC-915 (made by Takeda Yakuhin Kogyo)

(Example 93) Oxazoline crosslinking agent Epocross WS-500 (made by Nippon Shokubai)

(Example 94) Monofunctional modified bisphenol A type epoxy emulsion Denacast EM-103 (Nagase Kasei Kogyo)

(Example 95)

The results of ~~the an~~ adhesion test of a sample, obtained by ~~internally~~-adding in the latex a surfactant as the carboxyl group blocking agent and chlorinating the outside surface, are shown in Table 16. The carboxyl group blocking agent used in the example is as follows.

Table 16

Example No.	Internally added carboxyl-group blocking agent	Trademark	Amount added (part)	Adhesion Test
95	β -naphthalenesulfonic acid-formaline condensation product	demol N	2.5	○

(Example 95) β -naphthalenesulfonic acid -formaline condensation product Demol N (made by Kao)

(Example 96)

The results of ~~the an~~ adhesion test of a sample, obtained by ~~internally~~-adding in the latex a hydrogen bond forming regulator as the carboxyl group blocking agent and chlorinating the outside surface, are shown in Table 17. The carboxyl group blocking agent used in the example is as follows.

(Example 96) Polyamidepolyurea resin Sumirez Resin 703 (made by Sumitomo Kagaku)

Table 17

Example No.	Internally added carboxyl-group blocking agent	Trademark	Amount added (part)	Adhesion Test
96	Polyamide polyurea resin	Sumirez resin 703	2.5	○

(Example 97)

The results of ~~the an~~ adhesion test of a sample, obtained by using a sizing agent as the carboxyl group blocking agent for treating the inside surface and by chlorinating

the outside surface, are shown in Table 18. The carboxyl group blocking agent used in the example is as follows.

(Example 97) Alkylketene dimer Hasize AK-720H (made by Harima Kasei)

Table 18

Example No.	Carboxyl-group blocking agent for surface treatment	Trademark	Concentration (%)	Adhesion Test
97	Alkylketene dimer	Hasize AK-720H	0.025	○

(Example 98)

The results of ~~the~~an adhesion test of a sample, obtained by using an organic crosslinking agent as ~~the~~carboxyl group blocking agent for treating the inside surface and ~~by~~ chlorinating the outside surface, are shown in Table 19. The carboxyl group blocking agent used in the example is as follows.

(Example 98) Blocked isocyanate Prominate XC-915 (made by Takeda Yakuhin Kogyo)

Table 19

Example No.	Carboxyl-group blocking agent for surface treatment	Trademark	Concentration (%)	Adhesion Test
98	Blocked isocyanate	Prominate XC-915	0.025	○

(Example 99)

The results of ~~the~~an adhesion test of a sample, obtained by using a hydrogen bond forming regulator as ~~the~~carboxyl group blocking agent for treating the inside surface and ~~by~~ chlorinating the outside surface, are shown in Table 20. The carboxyl group blocking agent used in the example is as follows.

(Example 99) Polyamide resin Sumirez Resin 5001 (made by Sumitomo Kagaku)

Table 20

Example No.	Carboxyl-group blocking agent for surface treatment	Trademark	Concentration (%)	Adhesion Test
99	Polyamide resin	Sumirez resin 5001	0.025	○

(Example 100)

The results of ~~the~~an adhesion test of a sample, obtained by using an aluminum compound as the carboxyl group blocking agent for treating the inside surface and ~~by~~ chlorinating the outside surface, are shown in Table 21. The carboxyl group blocking agent used in the example is as follows.

(Example 100) Polyaluminumhydroxide Paho#2S (made by Asada Kagaku Kogyo)

Table 21

Example No.	Carboxyl-group blocking agent for surface treatment	Trademark	Concentration (%)	Adhesion Test
100	Polyaluminumhydroxide	Paho#2S	0.025	○

As ~~seen from~~shown in the above examples, ~~any of all~~ the carboxylated latex films made according to the present invention ~~was~~were non-adhesive.

{Industrial Applicability}

The present invention provides a powder-free ~~and~~₂ non-adhesive latex product obtained by adding a carboxyl-group blocking agent into a carboxylated latex, or₂ alternatively₂ by providing a layer treated with the carboxyl-group blocking agent to one or both surfaces of the carboxylated latex product. The present invention also enables ~~to~~for the manufacture of a non-adhesive latex product having excellent durability if the carboxylated latex contains an internally added aluminum type inorganic crosslinking agent, such as aluminate or aluminum hydroxide gel. In the case of a fingerstall, a non-powdered machine-wound product can be prepared on-machine by utilizing ~~non-adhesion of the~~ non-adhesive product.

CLAIMS

1. A non-adhesive carboxylated latex product incorporated with a carboxyl-group blocking agent.
2. A non-adhesive carboxylated latex product having a layer treated with a carboxyl-group blocking agent on one or both surfaces of a carboxylated latex product or a carboxylated latex product incorporated with a carboxyl group blocking agent.
3. A non-adhesive carboxylated latex product having a layer treated with a carboxyl group blocking agent on the inside surface of a carboxylated latex product or a carboxylated latex product incorporated with a carboxyl group blocking agent and having a chlorination treatment on the outside surface.
4. A non-adhesive carboxylated latex product according to claim 1 to claim 3, wherein the carboxylated latex is NBR, SBR, CR or MBR.
5. A durable, non-adhesive carboxylated latex product according to any one of claims 1 to 4, wherein the carboxylated latex is added with an internally added aluminum type inorganic crosslinking agent and is crosslinked therewith.
6. A non-adhesive carboxylated latex product according to any one of claims 1 to 5, wherein the latex product is a dip product.
7. A non-adhesive carboxylated latex product according to claim 6, wherein the dip product is a fingerstall, gloves, balloon or condom.
8. A non-adhesive carboxylated latex product according to any one of claims 1 to 7, wherein the carboxyl-group blocking agent is a metal element crosslinking agent having three or more valences.
9. A non-adhesive carboxylated latex product according to claim 8, wherein the metal element crosslinking agent having three or more valences includes at least one selected from aluminum, titanium or zirconium compounds.
10. A non-adhesive carboxylated latex product according to any one of claims 1 to 7, wherein the carboxyl-group blocking agent is an organic crosslinking agent for the carboxyl group of the carboxylated latex.
11. A non-adhesive carboxylated latex product according to claim 10, wherein the organic crosslinking agent for the carboxyl group includes at least one selected from aziridine compounds, epoxy compounds, blocked isocyanates, oxazoline

compounds, carbodiimido compounds, melamineformaldehyde resins, ureaformaldehyde resins, isocyanates, phenolformaldehyde resins, glycols, polyols, diamines, polyamines, hexamethoxymethylmelamines and methylolacrylamides.

12. A non-adhesive carboxylated latex product according to any one of claims 1 to 7, wherein the carboxyl-group blocking agent includes at least one selected from glyoxals, polyamide compounds, polyamide polyurea compounds, polyamine polyurea compounds, polyamideamine polyurea compounds, polyamide polyurea glyoxal condensation reaction products, polyamideamine compounds, polyamideamine epihalohydrine condensation reaction products, polyamideamine formaldehyde condensation reaction products, polyamine epihalohydrine condensation reaction products, polyamine formaldehyde condensation reaction products, polyamide polyurea epihalohydrine condensation reaction products, polyamide polyurea formaldehyde condensation reaction products, polyamine polyurea epihalohydrine condensation reaction products, polyamine polyurea formaldehyde condensation reaction products, polyamideamine polyurea epihalohydrine condensation reaction products, and polyamideamine polyurea formaldehyde condensation reaction products.

13. A non-adhesive carboxylated latex product according to any one of claims 1 to 7, wherein the carboxyl-group blocking agent includes at least one selected from monofunctional amines, monofunctional epoxy compounds, monofunctional isocyanates and monofunctional blocked isocyanates.

14. A non-adhesive carboxylated latex product according to any one of claims 1 to 7, wherein the carboxyl-group blocking agent is a sizing agent.

15. A non-adhesive carboxylated latex product according to any one of claims 1 to 7, wherein the carboxyl-group blocking agent is a non-adhesive surfactant.

16. A method for producing a non-adhesive carboxylated latex product according to any one of claims 1 to 15, characterized in that one or both surfaces of the latex product are brought into contact with one or more of the carboxyl-group blocking agent solutions defined in any of claims 8 to 15 to attach the carboxyl-group blocking agent to the latex surface.

17. A method for producing a non-adhesive carboxylated latex dip product, characterized in that there is used a solution of a mono- or bi-valent external coagulant for carboxylated latex which is mixed with or dissolved in one or more of the carboxyl

group blocking agents defined in any of claims 8 to 15.

18. A method for producing a non-adhesive carboxylated latex dip product, characterized in that a dipping former is dipped and deposited with one or more of the carboxyl-group blocking agents defined in claims 8 to 15, dipped and deposited with a mono- or bi-valent external coagulant, and then dipped in a latex.

19. A method for producing a non-adhesive carboxylated latex dip product, characterized in that a dipping former is dipped and deposited with one or more of the carboxyl-group blocking agents defined in any of claims 8 to 15, then dipped in a latex liquid to form a latex film, further dipped in a mono- or bi-valent external coagulant solution, and subsequently dipped in the carboxylated latex again.

20. A method for producing a non-adhesive carboxylated latex dip product, characterized in that a dipping former is dipped in a mixture of one or more of the carboxyl-group blocking agents defined in any of claims 8 to 15 and a carboxylated latex stable to the blocking agent to form a latex film, further dipped in a mono- or bi-valent external coagulant solution, and thereafter dipped in the carboxylated latex liquid again.

21. A method for producing a non-adhesive carboxylated latex dip product, characterized in that a dipping former is dipped in a mono- or bi-valent coagulant suspension for carboxylated latex which contains, as the carrier, fine powder of one or more of the carboxyl-group blocking agents defined in any of claims 8 to 15 that is hardly soluble or insoluble in water or alcohol, and subsequently dipped in the carboxylated latex liquid.

22. A non-adhesive fingerstall, wherein the fingerstall defined in claim 7 has a shape mechanically wound from the mouth before removed from the dipping former.

23. A non-adhesive fingerstall according to claim 7 or claim ~~2222~~, which has a wound mouth.

24. A method for producing a non-adhesive fingerstall with wound mouth according to claim 23, characterized in that an adhesive portion is provided on the upper part at the time of dipping and then winding is conducted.

25. A method for producing a non-adhesive fingerstall according to claim 7 or claim 22, characterized in that the outside surface is treated with a carboxyl group blocking agent after a wound mouth is provided.

ABSTRACT

The object of the present invention is to provide a non-adhesive clean latex product and a method for manufacturing the same. A non-adhesive clean emulsion latex product is manufactured by adding a carboxyl-group blocking agent to a carboxylated latex or by providing a layer treated with the carboxyl-group blocking agent on one or both surfaces of a film of the carboxylated latex. Further, a non-adhesive, easy-to-wear-and-remove emulsion latex product is manufactured by affording a layer treated with a carboxyl group blocking agent on the inside surface of a carboxylated latex film and providing a chlorination treatment on the outside thereof. Furthermore, a sulfur-free, highly durable latex product can be manufactured by adding an aluminate or an aluminumhydroxide gel to the latex. The present invention also provides a non-powdered, clean, on-machine wound fingerstall.